

## A Self-Conditioner for Resin-Modified Glass Ionomers in Bonding Orthodontic Brackets

Samir E. Bishara<sup>a</sup>; Adam W. Ostby<sup>b</sup>; John Laffoon<sup>b</sup>; John J. Warren<sup>c</sup>

### ABSTRACT

**Objective:** To evaluate a new self-etch conditioner used with resin-modified glass ionomers (RMGIs) in bonding orthodontic brackets.

**Materials and Methods:** Sixty human molars were cleaned, mounted, and randomly divided into three groups. In group 1 (control), 20 orthodontic brackets were bonded to teeth using Transbond Plus Self-etching Primer; in group 2, 20 brackets were bonded using an RMGI with a 10% polyacrylic acid conditioner. In group 3, 20 brackets were bonded using Fuji Ortho LC with a new no-rinse self-conditioner for RMGIs. The same bracket type was used on all groups. The teeth were debonded in shear mode using a universal testing machine, and the amount of residual adhesive remaining on each tooth was evaluated. Analysis of variance was used to compare the shear bond strength (SBS), and the  $\chi^2$  test was used to compare the Adhesive Remnant Index (ARI) scores.

**Results:** There were no significant differences in the SBS ( $P = .556$ ) between the groups. The mean SBS for Transbond Plus was  $8.6 \pm 2.6$  MPa, for Fuji Ortho LC using 10% polyacrylic acid  $9.1 \pm 4.6$  MPa, and for Fuji Ortho LC using GC Self-conditioner  $9.9 \pm 4.1$  MPa. The comparisons of the ARI scores between the three groups ( $\chi^2 = 35.5$ ) indicated that bracket failure mode was significantly different ( $P < .001$ ), with more adhesive remaining on the teeth bonded using Transbond.

**Conclusions:** The new self-etch conditioner can be used with an RMGI to successfully bond brackets. In addition, brackets bonded with Fuji Ortho LC resulted in less residual adhesive remaining on the teeth.

**KEY WORDS:** Self-etch; Resin-modified glass ionomer; Bonding; Brackets

### INTRODUCTION

In their attempt to minimize the incidence of decalcification around orthodontic appliances, orthodontists have always emphasized the need for good oral hygiene<sup>1</sup> as well as the role of fluoride in preventing caries.<sup>2,3</sup> As a result, the application of fluoride solutions topically to the etched tooth during bonding and the use of fluoride rinses during treatment are recom-

mended.<sup>4</sup> In addition, several fluoride-releasing cements have been developed and used clinically to reduce decalcification.<sup>5-7</sup>

Glass ionomer cements (GICs) were initially introduced as orthodontic bonding adhesives to take advantage of some of their desirable characteristics, namely, their ability to chemically bond to tooth structure<sup>8,9</sup> and sustain fluoride release following bonding.<sup>10-17</sup> Fluoride release was shown to increase in the plaque adjacent to brackets bonded with GICs,<sup>18</sup> but their use in orthodontics was limited because of their lower bond strengths.<sup>19-25</sup> In an attempt to increase the bond strengths of GICs, resin particles were added to their formulation to create resin-modified glass ionomers (RMGIs). These adhesives release fluoride-like conventional GICs and were used to bond orthodontic brackets because of their relatively higher bond strengths.<sup>26-31</sup> However, RMGIs have lower shear bond strength (SBS) compared to composite resins,<sup>32-35</sup> particularly within the first half hour after bond-

<sup>a</sup> Professor, Orthodontic Department, College of Dentistry, University of Iowa, Iowa City.

<sup>b</sup> Research Assistants, College of Dentistry, University of Iowa, Iowa City.

<sup>c</sup> Associate Professor, Department of Preventive and Community Dentistry, University of Iowa, Iowa City.

Corresponding author: Dr Samir E. Bishara, Orthodontic Department, College of Dentistry, S219 DSB, University of Iowa, Iowa City, IA 52242 (e-mail: karla-starckovich@uiowa.edu).

Accepted: September 2006. Submitted: July 2006.

© 2007 by The EH Angle Education and Research Foundation, Inc.

ing,<sup>36</sup> but they are still able to bond orthodontic brackets successfully.<sup>34-38</sup> In addition, in vivo studies have shown no significant differences in bracket failure rates between the two adhesive groups.<sup>32</sup> In an effort to improve the SBS of RMGIs on orthodontic brackets, various enamel conditioners have been evaluated for use with RMGIs. It was observed that teeth conditioned with 10% polyacrylic acid had an SBS that was significantly lower than teeth conditioned with 37% phosphoric acid before bonding with RMGIs.<sup>39,40</sup> Increasing the polyacrylic acid concentration to 20% resulted in an eightfold increase in SBS; however, this SBS was still significantly lower than that of teeth conditioned with phosphoric acid.<sup>40</sup> Although self-etching primers (SEPs) are typically designed for use with composite resins, a recent study evaluated using an SEP with an RMGI to bond brackets. Greater bond strengths were observed in teeth conditioned with the SEP when compared to teeth conditioned with either 10% polyacrylic acid or 37% phosphoric acid etchants.<sup>41</sup>

While conventional SEPs have been marketed for use with composite resins, a new no-rinse self-conditioner (GC Self-conditioner; GC America, Alsip, Ill) has been developed for use specifically with RMGI restorative materials. When used on enamel and dentin, this self-etch conditioner produced a similar microtensile bond strength as that obtained with a 25% polyalkenoic acid conditioner,<sup>42</sup> with the added advantage of not having to be rinsed off following application. However, its ability to bond orthodontic brackets when used with an RMGI has not been evaluated. Thus, the purpose of this study was to determine if the new self-conditioner designed for use with an RMGI could successfully be used to bond orthodontic brackets by providing an acceptable SBS.

## MATERIALS AND METHODS

### Teeth

Sixty freshly extracted human molars were collected and stored in a solution of 0.2% (weight/volume) thymol. To meet the criteria for use in the study, the teeth were selected only if they had intact buccal enamel, had not been pretreated with chemical agents (eg, H<sub>2</sub>O<sub>2</sub>), had no surface cracks from extraction forceps, and were free of caries. The teeth were embedded in dental stone placed in phenolic rings (Buehler Ltd, Lake Bluff, Ill).

A mounting jig was used to align the facial surfaces of the teeth perpendicular with the bottom of the mold. This kept the buccal surface of the tooth parallel to the applied force during the shear test. Following mounting, the teeth were cleaned and polished with pumice and rubber prophylactic cups for 10 seconds.

### Brackets

Orthodontic lateral incisor metal brackets of the Victory series (3M Unitek, Monrovia, Calif) were used in the study. The average surface area of the bracket base was determined to be 10.3 mm<sup>2</sup>. This was determined by randomly measuring five bracket bases.

### Groups Tested

*Group 1 (control).* Twenty teeth were bonded with precoated APC Plus metal brackets (3M Unitek) using the Transbond Plus Self-etching Primer system. Transbond Plus uses a lollipop system that has two compartments: one contains methacrylated phosphoric acid esters, initiators, and stabilizers, while the other compartment contains water, fluoride complexes, and stabilizers. To activate the product, the two compartments were squeezed so that the contents of each compartment were allowed to mix. The resulting mix was then applied to the tooth surface for 3 to 5 seconds. The SEP was lightly dried with compressed air for 2 seconds. Each bracket was applied to the tooth using a 300-g force (Correx force gauge, Bern, Switzerland) to ensure a uniform thickness of adhesive. Excess adhesive was removed with a sharp scaler, and the bracket was light cured with a halogen light for 20 seconds.

*Group 2.* Twenty teeth were etched using 10% polyacrylic acid enamel conditioner. Following the manufacturers' instructions, the conditioner was applied for 20 seconds, and the tooth was then thoroughly rinsed with water. Excess water was blotted away using a moist cotton roll. The capsules containing the RMGI Fuji Ortho LC were activated and triturated at 4000 rpm for 10 seconds. Capsules were placed in the GC Capsule Applier (GC America Inc) to place the adhesive on each bracket. Excess adhesive was removed using a sharp scaler, and the bracket was light cured with a halogen light for 40 seconds (10 seconds each from the mesial, distal, occlusal, and gingival sides).

*Group 3.* On the remaining 20 teeth, the new self-conditioner designed to be used with RMGIs, GC Self-conditioner (GC America Inc), was used to prepare the enamel surfaces for bonding. This self-conditioner contains 2-hydroxyethyl methacrylate, 4-methacryloxyethyltrimellitate anhydride, ethanol, and water. Following the manufacturers' instructions, a thin layer of the self-conditioner was applied to the enamel surface with a micro-tip applicator and left undisturbed for 10 seconds. The surface was then dried using compressed air for 5 seconds. The capsules containing the RMGI Fuji Ortho LC were activated and triturated similar to group 2. The adhesive was applied to the bracket, and the teeth were light cured as described for group 2.

**Table 1.** Descriptive Statistics in Megapascals (MPa) and the Results of the Analysis of Variance for the Comparisons Between the Three Groups Tested<sup>a</sup>

Group	Conditioner	Adhesive	n	$\bar{x}$	SD	Range
1	Transbond Plus	Composite resin	20	8.6	2.6	3.4–12.0
2	10% polyacrylic acid	RMGI	20	9.1	4.6	1.2–15.2
3	GC Self-conditioner	RMGI	20	9.9	4.1	0.2–18.2

<sup>a</sup>  $\bar{x}$  = mean; SD = standard deviation; P = probability; RMGI = resin-modified glass ionomer. *F* ratio = 0.59; *P* = .556.

## Debonding Procedure

The SBS of each group was determined within half an hour from the time of bonding, to simulate the clinical conditions when arch wires are first tied to newly bonded teeth. A steel rod with a flattened end was attached to the cross-head of a Zwick testing machine (Zwick GmbH, Ulm, Germany). The rod applied an occlusogingival load to test the bracket-tooth interface in a shear mode to the complete failure of the bonded bracket. The results of each test were recorded by a computer that was electronically connected to the testing machine. The Zwick machine (cell capacity = 50 kN) recorded the results from each test in megapascals (MPa) at a cross-head speed of 5.0 mm/min.

## Adhesive Remnant Index

Once the brackets were debonded, the enamel surface of each tooth was examined under  $\times 10$  magnifications to determine the amounts of residual adhesive remaining on each tooth. A modified Adhesive Remnant Index (ARI) was used to quantify the amount of remaining adhesive using the following scale: 1 = all the adhesive remained on the tooth, 2 = more than 90% of the adhesive remained on the tooth, 3 = between 10% and 90% of the adhesive remained on the tooth, 4 = less than 10% of the adhesive remained on the tooth, and 5 = no adhesive remained on the tooth.

## Statistical Analysis

An analysis of variance was used to determine whether there was a significant difference in SBSs between the three test groups. A  $\chi^2$  test was used to compare the bond failure mode (ARI scores) between the three groups. For the purpose of statistical analysis, the ARI scores 1 and 2 as well as 4 and 5 were combined. Significance for all statistical tests was predetermined at  $P \leq .05$ .

## RESULTS

### Shear Bond Strength

The descriptive statistics including the mean, standard deviation, and minimum and maximum values for the three groups are presented in Table 1. The mean SBS for the brackets bonded using the Transbond

**Table 2.** Frequency Distribution of the Modified Adhesive Remnant Index (ARI) Scores and the Result of the  $\chi^2$  Comparisons Between the Three Groups Tested<sup>a</sup>

Group	n	Modified ARI Scores <sup>b</sup>				
		1	2	3	4	5
1	20	12	5	2	1	—
2	20	1	—	2	8	9
3	20	—	3	2	7	8

<sup>a</sup>  $\chi^2 = 35.5$ ;  $P < .001$ .

<sup>b</sup> 1 indicates all composite remained on the tooth; 2, more than 90% of the composite remained on the tooth; 3, 10% to 90% of the composite remained on the tooth; 4, less than 10% of the composite remained on the tooth; 5, no composite remained on the tooth.

Plus system was  $8.6 \pm 2.6$  MPa; for the traditional 10% polyacrylic acid conditioner + RMGI,  $9.1 \pm 4.6$  MPa; and for the new self-conditioner + RMGI,  $9.9 \pm 4.1$  MPa. The results of the analysis of variance ( $F = 0.59$ ) indicated there were no statistically significant differences ( $P = .556$ ) between the groups.

## Adhesive Remnant Index

The failure modes of the three groups are presented in Table 2. The  $\chi^2$  comparisons of the ARI scores between the three groups ( $\chi^2 = 35.5$ ) indicated that bracket failure modes were significantly different ( $P < .001$ ). In the Transbond group, most of the bond failure was at the bracket/adhesive interface (groups 1 and 2), while in both groups bonded with the RMGI, the bond failure was at the enamel-adhesive interface (groups 4 and 5).

## DISCUSSION

Traditional methods of bonding orthodontic brackets to teeth have relied on the use of the acid-etch technique to achieve adequate retention. The bonding procedure can be improved by minimizing enamel loss, decreasing enamel demineralization adjacent to brackets, and decreasing technique sensitivity while still providing adequate SBS. With such advances, the clinician can effectively reduce chair time and increase cost-effectiveness, resulting in increased convenience and reduced costs for the patient.

RMGIs have been used as bracket-bonding adhesives because of their fluoride-releasing capabilities

and ability to bond orthodontic brackets with acceptable SBS.<sup>10,17,32,34–38</sup> This study evaluated the use of a new self-etch conditioner with an RMGI in bonding brackets. The findings from this study indicated that the brackets bonded with this new conditioner and the RMGI Fuji Ortho LC had a mean SBS of  $9.9 \pm 4.1$  MPa. This value was similar to the SBS of brackets bonded using Fuji Ortho LC with its recommended 10% polyacrylic acid conditioner (mean of  $9.1 \pm 4.6$  MPa) as well as those bonded with a composite control, Transbond XT Plus (mean of  $8.6 \pm 2.6$  MPa). It has been suggested that an SBS of 6.0 to 8.0 MPa is adequate for bonding orthodontic brackets to teeth.<sup>43,44</sup> The present findings indicate that all three groups tested in this study have reached this ideal range within the first half-hour following bonding. While earlier reports indicated that RMGIs have lower SBS than composite resins do,<sup>32–36</sup> especially in the first half-hour following bonding,<sup>36</sup> the present findings indicated that an RMGI used with either the new self-etch conditioner or the recommended conditioner provided a comparable SBS to that of the composite control. In addition, it was recently shown that following thermocycling, the SBSs of brackets bonded using an RMGI and a composite resin were not significantly different.<sup>45</sup>

The present results also indicated that the brackets bonded using Fuji Ortho LC failed in a different mode than those bonded using the Transbond adhesive system. In general, bond failure for brackets bonded using Fuji Ortho LC with either conditioner occurred at the enamel-adhesive interface, while brackets bonded using Transbond typically failed at the bracket-adhesive interface. Bracket failure at each of the two interfaces has its own advantages and disadvantages. As an example, bracket failure at the bracket-adhesive interface is advantageous since it leaves the enamel surface relatively intact. However, considerable chair time is needed to remove the residual adhesive, with the added possibility of damaging the enamel surface during the cleaning process.<sup>46</sup> On the other hand, when brackets fail at the enamel-adhesive interface, less residual adhesive remains, but the probability of damage to the enamel surface is increased when failure occurs in this mode.<sup>47</sup>

In summary, RMGIs provide the advantages of sustained fluoride release and can be used in a moist environment to bond brackets. In addition, the new self-etch conditioner tested offers the added benefit of not needing to be rinsed off following application. However, RMGIs need a longer curing time than most composite resin bonding systems do. The clinician should weigh the advantages and disadvantages of each bonding system when choosing an orthodontic bracket adhesive.

## CONCLUSIONS

- Brackets bonded with the new self-conditioner had an SBS that was comparable to brackets bonded using both an RMGI with its recommended conditioner and brackets bonded with a composite resin.
- The new self-etch conditioner has the added benefit of not needing to be rinsed off and may reduce technique sensitivity in the bonding process.

## ACKNOWLEDGMENTS

The authors would like to express their appreciation to 3M Unitek and GC America for providing the materials for this study.

## REFERENCES

1. Shannon IL. Prevention of decalcification in orthodontic patients. *J Clin Orthod.* 1981;15:694–706.
2. Schrotenboer GH. Fluoride benefits—after 36 years. *J Am Dent Assoc.* 1981;102:473–474.
3. Carlos JP. The prevention of dental caries: ten years later. *J Am Dent Assoc.* 1982;104:193–197.
4. Bishara SE, Chan D, Abadir EA. The effects on the bonding strength of fluoride application after etching. *Am J Orthod Dentofacial Orthop.* 1989;95:259–260.
5. Skibell RB, Shannon IL. Addition of stannous fluoride to orthodontic cement. *Int J Orthod.* 1973;11:131–135.
6. Sadowsky PL, Retief DH, Bradley EL. Enamel fluoride uptake from orthodontic cement and its effect on demineralization. *Am J Orthod.* 1981;79:523–534.
7. Rezich PM, Panneton MJ, Barkmeier WW. In vitro evaluation of fluoride and non-fluoride releasing orthodontic adhesives on bracket bond strength. *J Esthet Dent.* 1989;1:101–104.
8. Kent BE, Lewis GG, Wilson AD. The properties of a glass ionomer cement. *Br Dent J.* 1973;135:322–326.
9. Hotz P, McClean JW, Sced I, Wilson AD. The bonding of glass ionomer cements to metal and tooth substrates. *Br Dent J.* 1977;242:41–47.
10. Arthur J, Bergland S. Clinical trials with crystal growth conditioning as an alternative to acid-etch enamel pretreatment. *Am J Orthod Dentofacial Orthop.* 1984;85:333–340.
11. Prosser HJ, Powis DR. The characterization of glass-ionomer cements: the physical properties of current materials. *J Dent Res.* 1984;12:231–240.
12. Causton BE. Bonding class II composite to etched glass-ionomer cement. *Br Dent J.* 1987;163:321–324.
13. Aboush YE, Jenkins CB. An evaluation of the bonding of a glass-ionomer restorative to dentin. *Br Dent J.* 1986;161:179–184.
14. Van Kijken JWV, Horsdt PM. A. In vivo adaptation of restorative materials to dentin. *J Prosthet Dent.* 1986;56:677–681.
15. Wilson AD, Groffman DM, Kuhn AT. The release of fluoride and other chemical species from a glass-ionomer cement. *Biomaterials.* 1985;6:431–434.
16. Swift EJ Jr. Effects of glass ionomers on recurrent caries. *Oper Dent.* 1989;14:40–43.
17. McCourt JW, Cooley RL, Huddleston AM. Fluoride release from fluoride-containing liners/bases. *Quintessence Int.* 1990;21:41–45.
18. Hallgren A, Oliveby A, Twetman S. Fluoride concentration in plaque adjacent to orthodontic brackets retained with glass ionomer cements. *Br J Orthod.* 1994;21:23–26.



19. Bishara SE, Gordan VV, VonWald L, Jakobsen JR. Shear bond strength of composite, glass, and acidic primer adhesive. *Am J Orthod Dentofacial Orthop.* 1999;115:24–28.
20. Klockowski R, Davis EL, Joynt RB, Wiczowski G, McDonald A. Bond strength and durability of glass ionomer cements used as bonding agents in the placement of orthodontic brackets. *Am J Orthod Dentofacial Orthop.* 1989;96:60–64.
21. Cook PA, Youngson CC. An in vitro study of bond strength of glass ionomer cement in the direct bonding of orthodontic brackets. *Br J Orthod.* 1988;15:247–253.
22. Fajen VB, Duncanson MG, Nanda RS, Currier GF, Angolkar PV. An in vitro evaluation of bond strength of three glass ionomer cements. *Am J Orthod Dentofacial Orthop.* 1990;97:316–322.
23. Wiltshire WA. Shear bond strengths of a glass ionomer for direct bonding in orthodontics. *Am J Orthod Dentofacial Orthop.* 1994;106:127–130.
24. Miquel JAM, Almeida MA, Chevitaese O. Clinical comparison between a glass ionomer cement and a composite for direct bonding of orthodontic brackets. *Am J Orthod Dentofacial Orthop.* 1995;107:484–487.
25. Miller JR, Mancl L, Arbuckle G, Baldwin J, Phillips RW. A three-year clinical trial using a glass ionomer cement for the bonding of orthodontic brackets. *Angle Orthod.* 1996;66:309–312.
26. Diaz-Arnold AM, Holmes DC, Wistrom DW, Swift EJ Jr. Short-term fluoride release/uptake of glass ionomer restoratives. *Dent Mater.* 1995;11:96–101.
27. Forsten L. Resin-modified glass ionomer cements: fluoride release and uptake. *Acta Odontol Scand.* 1995;53:222–225.
28. Forss J. Release of fluoride and other elements from light-cured glass ionomers in neutral and acidic conditions. *J Dent Res.* 1993;72:1257–1262.
29. Forsten L. Fluoride release of glass ionomers. *J Esthet Dent.* 1994;6:216–222.
30. McCourt JW, Cooley RL, Barnwell S. Bond strength of light-cure fluoride-releasing base-liners as orthodontic bracket adhesives. *Am J Orthod Dentofacial Orthop.* 1991;100:47–52.
31. Komori A, Ishikawa H. Evaluation of a resin-reinforced glass ionomer cement for use as an orthodontic bonding agent. *Angle Orthod.* 1997;3:189–195.
32. Summers A, Kao E, Gilmore J, Gunel E, Ngan P. Comparison of bond strength between a conventional resin adhesive and a resin-modified glass ionomer adhesive: an in vitro and in vivo study. *Am J Orthod Dentofacial Orthop.* 2004;126:200–206.
33. Komori A, Ishikawa H. Evaluation of a resin-reinforced glass ionomer cement for use as an orthodontic bonding agent. *Angle Orthod.* 1997;67:189–195.
34. Rix D, Foley TF, Mamandras A. Comparison of bond strength of three adhesives: composite resin, hybrid GIC, and glass-filled GIC. *Am J Orthod Dentofacial Orthop.* 2001;119:36–42.
35. Coups-Smith KS, Rossouw PE, Titley KC. Glass ionomer cements as luting agents for orthodontic brackets. *Angle Orthod.* 2003;73:436–444.
36. Bishara SE, VonWald L, Olsen ME, Laffoon JF. Effect of time on the shear bond strength of glass ionomer and composite orthodontic adhesives. *Am J Orthod Dentofacial Orthop.* 1999;116:616–620.
37. Fricker JP. A 12-month clinical evaluation of a light-activated glass polyalkenoate (ionomer) cement for the direct bonding of orthodontic brackets. *Am J Orthod.* 1994;105:502–505.
38. Silverman E, Cohen M, Demke R, Silverman M. A new light-cured glass ionomer cement that bonds brackets to teeth without etching in the presence of saliva. *Am J Orthod.* 1995;108:231–236.
39. Bishara SE, Vonwald L, Laffoon JF, Jakobsen JR. Effect of altering the type of enamel conditioner on the shear bond strength of a resin-reinforced glass ionomer adhesive. *Am J Orthod Dentofacial Orthop.* 2000;118:288–294.
40. Bishara SE, VonWald L, Laffoon JF, Jakobsen JR. Effect of changing enamel conditioner concentration on the shear bond strength of a resin-modified glass ionomer adhesive. *Am J Orthod Dentofacial Orthop.* 2000;118:311–316.
41. Cacciafesta V, Sfondrini MF, Baluga L, Scribante A, Klersy C. Use of a self-etching primer in combination with a resin-modified glass ionomer: effect of water and saliva contamination on shear bond strength. *Am J Orthod Dentofacial Orthop.* 2003;124:420–426.
42. Coutinho E, Van Landuyt K, De Munck J, et al. Development of a self-etch adhesive for resin-modified glass ionomers. *J Dent Res.* 2006;85:349–353.
43. Øgaard B, Bishara SE, Duschner H. Enamel effects during bonding-debonding and treatment with fixed appliances. In: TM Graber, T Eliades, AE Athanasiou, eds. *Risk Management in Orthodontics: Experts' Guide to Malpractice.* Chicago, Ill: Quintessence; 2004:19–46.
44. Powers JM, Messersmith ML. Enamel etching and bond strength. In: Brantley WA, Eliades T, eds. *Orthodontic Materials: Scientific and Clinical Aspects.* Stuttgart, Germany: Thieme; 2001;105–122.
45. Bishara SE, Ostby AW, Laffoon JF, Warren JJ. Shear bond strengths of two adhesive systems following thermocycling. *Angle Orthod.* In press.
46. Bishara SE, VonWald L, Laffoon JF, Jacobsen JR. Effect of altering the type of enamel conditioner on the shear bond strength of a resin-reinforced glass ionomer adhesive. *Am J Orthod Dentofacial Orthop.* 2000;118:288–294.
47. Britton JC, McInnes P, Weinberg R, Ledoux WR, Retief DH. Shear bond strength of ceramic orthodontic brackets to enamel. *Am J Orthod Dentofacial Orthop.* 1998;114:243–247.