

STABILIZATION AND
SOLIDIFICATION OF

Hazardous, Radioactive, and Mixed Wastes

3RD VOLUME

T. Michael Gilliam and
Carlton C. Wiles, editors

STP 1240



STP 1240

*Stabilization and Solidification of
Hazardous, Radioactive, and
Mixed Wastes*

T. Michael Gilliam and Carlton C. Wiles, Editors

ASTM Publication Code Number (PCN):
04-012400-56



ASTM
100 Barr Harbor Drive
West Conshohocken, PA 19078
Printed in U.S.A.

ISBN: 0-8030-2020-6
PCN: 04-012400-56
ISSN: 1050-423x

Downloaded from http://asmedigitalcollection.asme.org/astm-ebook/book/chapter-pdf/7201155/10_1520_sip14100s.pdf by guest on 20 September 2024

Copyright © 1996 AMERICAN SOCIETY FOR TESTING AND MATERIALS, West Conshohocken, PA. All rights reserved. This material may not be reproduced or copied, in whole or in part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of the publisher.

Photocopy Rights

Authorization to photocopy items for internal, personal, or educational classroom use, or the internal, personal, or educational classroom use of specific clients, is granted by the American Society for Testing and Materials (ASTM) provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923; Tel: (508) 750-8400; online: <http://www.copyright.com/>.

Peer Review Policy

Each paper published in this volume was evaluated by three peer reviewers. The authors addressed all of the reviewers' comments to the satisfaction of both the technical editor(s) and the ASTM Committee on Publications.

To make technical information available as quickly as possible, the peer-reviewed papers in this publication were prepared "camera-ready" as submitted by the authors.

The quality of the papers in this publication reflects not only the obvious efforts of the authors and the technical editor(s), but also the work of these peer reviewers. The ASTM Committee on Publications acknowledges with appreciation their dedication and contribution to time and effort on behalf of ASTM.

Printed in Fredericksburg, VA
March 1996

Foreword

This publication, *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes: 3rd Volume* contains papers presented at the symposium of the same name, held in Williamsburg, Virginia on 1-5 November 1993. The symposium was sponsored by ASTM Committee D-34 on Waste Management; Oak Ridge National Laboratory; U.S. Environmental Protection Agency; Hazardous Substance Management Research Center of the New Jersey Institute of Technology; Environmental Canada Wastewater Technology Center; and the Alberta Environmental Center. T. Michael Gilliam of the Oak Ridge National Laboratory in Oak Ridge, Tennessee and Carlton C. Wiles of the National Renewable Energy Lab in Golden, Colorado presided as symposium chairmen and are editors of the resulting publication.

Contents

Overview	x
----------	---

INVITED PRESENTATIONS

Basic Considerations in the Application of Vitrification Technologies— I. L. PEGG	3
---	---

ORGANIC WASTES

Laboratory Equipment and Data Interpretation Method for Predicting Volatile Emissions During Solidification— H. J. J. SU, R. H. JENSEN, AND M. HINSEVELD	21
--	----

Evaluation of Solidification/Stabilization for Treating Explosives Contaminated Soils— M. J. CULLINANE, JR. AND M. CHANNELL	38
--	----

Immobilization of Low Level Hazardous Organics Using Recycled Materials— J. R. CONNER AND F. G. SMITH	52
--	----

Morphology and pH Changes in Leached Solidified/Stabilized Waste Forms— K. Y. CHENG AND P. L. BISHOP	73
--	----

MECHANISMS OF CONTAINMENT

Mechanisms of Metal Containment Resulting from the Solidification of a Commercially Produced Stabilized Waste— C. R. CHEESEMAN, C. J. SOLLARS, AND R. PERRY	80
---	----

Chemical Characterization of Pore Water of a Solidified Hazardous Waste— S. TRUSSELL AND B. BATCHELOR	94
---	----

Microbially Influenced Degradation of Cement-Solidified Low-Level Radioactive Waste Forms— R. D. ROGERS, M. A. HAMILTON, R. H. VEEH, AND J. W. McCONNELL, JR.	116
---	-----

PROCESS TECHNOLOGY DEVELOPMENT AND EVALUATION—PART I

Influence of Silica Fume on the Immobilization Properties of Cementitious Mortars Exposed to Freeze-Thaw Cycles— R. QUARESIMA, G. SCOCCIA, R. VOLPE, F. MEDICI, AND C. MERLI	135
--	-----

Stabilization of Heavy Metals in Portland Cement Matrix: Effects on Paste Properties—J. I. BHATTY AND P. B. WEST	147
Alkali-Slag Cements for the Immobilization of Radioactive Wastes—C. SHI AND R. L. DAY	163
Evaluation of Alternative Drilling Technologies and Subsurface Confinement Barriers for Single Shell Tanks at Hanford—W. P. ACHESON, T. A. TOWERS, K. W. WENTZEL, H. R. JOHNSON, AND W. K. OVERBEY	174
Performance of Cementitious Containment Barriers—M. L. ALLAN AND L. E. KUKACKA	186
Preliminary Tests of an Infrared Process Monitor for Polyethylene Encapsulation of Radioactive Waste—K. L. WRIGHT, R. W. JONES, J. F. McCLELLAND, AND P. D. KALB	198
Remediation of Lead-Contaminated Soils at Small Arms Ranges—A. R. GAVASKAR, J. L. MEANS, J. C. HEATH, AND B. NELSON	209
The Effect of Graphite Venting on ISV Processing of Low Permeability Soils—B. M. GARDNER AND R. K. FARNSWORTH	224
Summary of U.S. EPA Research on Solidified/Stabilized Waste Form Long-Term Durability—D. R. KIRK	239
Using Mixture Experiments to Develop Cementitious Waste Forms—R. D. SPENCE, C. M. ANDERSON, AND G. F. PIEPEL	251
Sulfur Polymer Cement, A Final Waste Form for Radioactive and Hazardous Wastes—G. R. DARNELL	272
EMERGING TECHNOLOGIES	
Lab-Scale Tests on ISV Vapor Transport Phenomena—R. K. FARNSWORTH AND B. M. GARDNER	285
Mixed Waste Solidification Testing on Polymer and Cement-Based Waste Forms in Support of Hanford's Wrap 2A Facility—D. A. BURBANK, JR. AND K. M. WEINGARDT	298
Vitrification of Lead Contained in Lead Based Organic Coatings Using Thermal Spray Technology—S. W. COVEY, J. P. PETREANU, AND A. KUMAR	311

Thermoplastic Encapsulation Treatability Study for a Mixed Waste Incinerator Off-Gas Scrubbing Solution— P. D. KALB, J. W. ADAMS, M. L. MEYER, AND H. H. BURNS	327
Critical Parameters and TCLP Performance of the RFP Microwave Solidification System— V. G. ESCHEN, G. S. FENNER, D. M. SPLETT, AND G. S. SPRENGER	341
Flow-Through Leach Testing Applied to Stabilized/Solidified Wastes— E. J. BUTCHER, C. R. CHEESEMAN, C. J. SOLLARS, AND R. PERRY	354
Property Changes of Cement-Based Waste Forms During Leaching— K. Y. CHENG AND P. L. BISHOP	375
Experimental and Theoretical Studies for Assessing the Retention Capacity of Cement Stabilized Materials for Land Disposal— S. BALZAMO, L. CASTELLANO, AND G. DE ANGELIS	388
Ultrasonic Agitation Method for Accelerating Batch Leaching Tests— R. J. CALDWELL, J. A. STEGEMANN, AND C. C. CHAO	413
PROCESS TECHNOLOGY DEVELOPMENT AND EVALUATION—PART II	
Evaluation of Contaminant Leachability Factors by Comparison of Treatability Study Data for Multiple Solidified/Stabilized Materials— P. M. ERICKSON AND E. F. BARTH	429
Summary of Technical Resource Document on Solidification/Stabilization and its Application to Waste Materials— J. L. MEANS, L. A. SMITH, K. W. NEHRING, S. E. BRAUNING, C. I. MASHNI, AND C. C. WILES	442
Bulk Site Reference Materials— J. J. BARICH, III AND R. R. JONES, SR.	454
Field Validation of Test Methods for Solidified Waste Evaluation—A Status Report— J. A. STEGEMANN, R. J. CALDWELL, AND C. SHI	467
Leaching Behavior of Polyethylene Encapsulated Nitrate Waste— M. FUHRMANN AND P. D. KALB	477
Stabilization/Solidification (S/S) of Heavy Metal Contaminated Soils by Means of a Quicklime-Based Treatment Approach— D. DERMATAS AND X. MENG	499

Recycling Contaminated Spent Blasting Abrasives in Portland Cement Mortars Using Solidification/Stabilization Technology— B. K. SALT, A. G. GARNER, D. W. FOWLER, R. C. LOEHR, AND R. L. CARRASQUILLO	514
Use of the Shrinking Core/Exposure Model to Describe the Leachability From Cement Stabilized Wastes— M. HINSEVELD AND P. L. BISHOP	528
Performance Modeling of Concrete/Metal Barriers Used in Low-Level Waste Disposal— R. SHUMAN, N. CHAU, A. S. ICENHOUR, H. W. GODBEE, AND M. L. THARP	540
Abrasive Blast Material Utilization in Asphalt Roadbed Material— J. L. MEANS, K. W. NEHRING, AND J. C. HEATH	569
Effects of Various Additives on the Solidification of Oily Sludges: A Bench-Scale Study— D. S. KEELY AND E. C. DIETHELM	584
In-Situ Slurry Wall Formation with the SoilSaw® Barrier System— E. E. CARTER	596
Literature Review of the Interaction of Select Inorganic Species on the Set and Properties of Cement and Methods of Abatement Through Waste Pretreatment— C. H. MATTUS AND A. J. MATTUS	609
Laser Driven Thermal Reactor for Hazardous Waste Stabilization— A. NAZARIAN	634
Volatilization Modeling of Semivolatile Organic Compounds During Solidification Processes— B. M. SASS, L. A. SMITH, W. M. C. HUANG, S. H. ROSANSKY, AND E. DRESCHER	648
FIELD APPLICATION AND FULL-SCALE TESTING	
In-Situ Stabilization of Mixed Waste Contaminated Soil— R. L. SIEGRIST, S. R. CLINE, T. M. GILLIAM, AND J. R. CONNER	667
Field Quality Control Strategies for Assessing Solidification/Stabilization— S. M. BUTLER, E. F. BARTH, AND J. J. BARICH	685
In Situ Solidification/Stabilization Pilot Study for the Treatment of Coal Tar Contaminated Soils and River Sediments— M. A. LAWSON, J. G. VENN, L. B. PUGH, AND T. VALLIS	691

Lysimeter Data as Input to Performance Assessment Models—

J. W. McCONNELL, JR., R. D. RODGERS, T. M. SULLIVAN, J. D. JASTROW, D. S. HICKS,
AND R. R. BREY

706

Author Index

725

Subject Index

727

Overview

Stabilization and solidification (S/S) technologies have been used for decades as a final treatment step prior to the disposal of both radioactive and chemically hazardous wastes. Stabilization refers to the alteration of waste contaminants to a more chemically stable form (i.e., a form which results in a greater difficulty of contaminant release to the environment), thereby resulting in a more environmentally acceptable waste form. Solidification refers to the physical alteration of the waste to restrict water release from or access to the waste and thereby resulting in a more environmentally acceptable waste form. Typically, stabilization processes also involve some form of physical solidification.

This symposium series (scheduled once approximately every three years) provides a forum for technical exchange between researchers working with S/S technologies from both the low-level radioactive and chemically hazardous waste communities. Although the two scientific communities are faced with similar problems and basically work with the same technologies, this symposium series presents a unique forum for technical exchange between the two communities. This meeting is the second in the series. Papers from the second meeting in the series were published in STP 1123, *Stabilization and Solidification of Hazardous, Radioactive, and Mixed Wastes*.

Land disposal restrictions are becoming ever increasingly stringent, driven by technical, regulatory, and political considerations. To the largest extent practicable, alternatives to land disposal are desirable, such as waste minimization, recycling, and destruction (e.g., incineration). In many instances, however, these alternatives are unrealistic due to the physical nature or location of the waste, the type and concentration of contaminants that it contains, or technical and economic issues. In such cases, S/S technology is a viable technical option which has historically proven to be cost effective.

A wide variety of both radioactive and chemically hazardous wastes are amenable to S/S. These include liquids, sludges, filter cakes, contaminated soils, and ash. S/S technologies are often used with chemically hazardous wastes contaminated with metals (e.g., lead, nickel, chromium) and are routinely used with low-level radioactive wastes of all types. Clearly, S/S is not the preferred technology for organic-rich wastes, but research is increasingly focusing on its application to wastes containing trace levels of organic contaminants.

S/S technologies are often classified on the basis of the principal additives used to obtain a solid matrix. Various systems based on organic and inorganic additives are listed below:

Inorganic Based Systems	Organic Based Systems
portland cement	bitumen
soluble silicates-cement	urea formaldehyde
pozzolan-lime	polybutadiene
pozzolan-cement	polyester
clay-cement	epoxy
gypsum	polyethylene

The specific technology used is based on several factors including volume increase, performance requirements, economics, logistic constraints, and material availability.

Inorganic-based systems may involve both stabilization and solidification. They generally utilize a hydraulic binder which reacts with water to form a solid product. Portland cement is the most commonly used binder. Cement-based systems are widely used due to the availability of raw materials, compatibility with existing process equipment, and adaptability to a variety of process configurations and waste-form performance requirements. Pure cement systems are becoming increasingly rare. Additives such as fly ash, granulated blast furnace slag, and specialty clays are used to improve waste-form performance and to minimize the cost. Compared with a pure cement system, these additives can reduce the resulting volume increase, reduce porosity (and, thus, reduce leachability), and increase compressive strength.

Organic-based systems consist of encapsulating the waste in a matrix that is essentially impervious to water. As such, they are designated as solidification processes. Many of these systems require water removal from the waste prior to solidification and thus result in an overall volume decrease. Products from these systems require a container to provide the necessary structural integrity to support overburden pressure. Use of such systems has been limited to special types of high-hazard, relatively low-volume, radioactive wastes due to the increased costs generally associated with these systems.

The scientific community has been focusing attention on understanding and predicting the long-term containment prospects of waste treated with this technology. Consequently, the majority of papers presented in this publication address to some degree one or both of the two principal issues associated with long-term containment; leachability and durability. Leach-bility refers to the release of contaminants from the waste form upon exposure to an aqueous media. Durability refers to the ability of the waste form to maintain its structural integrity upon exposure to expected environmental conditions.

ISBN 0-8032-2020-6