

- 6 "Bearings, Plain, Self-Aligning, Self-Lubricating, Low Speed Oscillation," MIL-B-81820C, 1976.
- 7 Mitchell, D. C., and Pratt, G. C., "Friction, Wear and Physical Properties of Some Filled PTFE Bearing Materials," Paper 101, I Mech E Lub and Wear Conf, London 1957, *Proceedings*, 1958, pp 416-423.
- 8 Pooley, C. M., and Tabor, D., "Friction and Molecular Structure: the Behaviour of Some Thermoplastics," *Proc Roy Soc*, A329, 1972, pp. 251-274.
- 9 Giltrow, J. P., and Lancaster, J. K., "The Friction and Wear of Carbon Fibre-Reinforced PTFE," *Proc AFML-MRI Conf on Solid Lubricants*, 1969, AFML-TR-60-127, 1970.
- 10 Harrison, M. B., "Plastic Fibre Materials," Paper 4, Conf on Plastics in Bearings, Solihull, 1973, *Plastics Inst*.
- 11 Play, D., "Les films intercalaires ou troisième corps en tribologie. Application à l'étude des paliers secs," Thèse, Fac Sci Lyon, 1974.
- 12 Godet, M., and Play, D., "Introduction to Tribology," Coll Int du CNRS, No. 233, Polymères et lubrification. Brest, CNRS, Paris, 1974, pp. 361-376.
- 13 Lancaster, J. K., "Polymer-Based Bearing Materials; the Role of Fillers and Fibre Reinforcements," *Tribology*, Vol. 5, 1972, pp. 249-255.
- 14 "Ampep X1; an Improved Bearing Material," *Ind Lub and Trib*, Vol. 27, 1975, pp. 54-56.
- 15 Floquet, A., Play, D., and Godet, M., "Surface Temperatures in Distributed Contacts. Application to Bearing Design," *ASME JOURNAL OF LUBRICATION TECHNOLOGY*, Vol. 99, pp. 277-283.
- 16 Pascoe, M. W., and Tabor, D., "The Friction and Deformation of Polymers," *Proc Roy Soc A235*, 1956, p. 210.
- 17 Allen, A. J. G., "Plastics as Solid Lubricants and Bearings," *Lub Eng*, Vol. 14, 1958, p. 211.
- 18 Steijn, R. P., "The Sliding Surface of Polytetrafluorethylene: An Investigation With the Electron Microscope," *Wear*, Vol. 12, 1968, p. 193.
- 19 Kinner, G. H., Pippett, J. S., and Atkinson, I. B., "A Laboratory Study of the Performance and Behaviour of Solid Film Lubricants Based on MoS₂ and Graphite Fluoride," RAE Technical Report 76026, 1976.
- 20 Lancaster, J. K., "The Friction and Wear of Non-Graphitic Carbons," *ASLE Trans*, Vol. 20, 1976, pp. 43-54.
- 21 Buckley, D. H. and Johnson, R. L., "Friction Wear and Decomposition Mechanics for Various Polymer Compositions in Vacuum to 10⁻⁹ mm of Mercury," NASA Technical Note D-2073, 1963.
- 22 Richardson, M. O. W., "Chemical Aspects of Wear Processes in Polymers—A Review," *Wear*, Vol. 17, 1971, pp. 89-99.
- 23 Pratt, G. C., "Plastics as Bearing Materials, With Particular Reference to PTFE," *Trans Plast Inst*, Vol. 32, 1964, pp. 255-260.
- 24 Briscoe, B. J., Pogolian, A. K., and Tabor, D., "The Friction and Wear of HDPE: The Action of Lead Oxide and Copper Oxide," *Wear*, Vol. 27, 1974, pp. 19-34.
- 25 Anderson, J. C., Private communication.
- 26 Tanaka, K., Uchiyama, Y., and Toyooka, S., "The Mechanism of Wear of Polytetrafluorethylene," *Wear*, Vol. 23, 1973, pp. 153-172.
- 27 Pratt, G. C., "Plastics-Based Bearings," Chapter 7, in *Lubrication and Lubricants*, Ed E. R. Braithwaite, Elsevier, 1967.
- 28 Evans, D. C., "Friction and Wear Properties of PTFE Composites at Elevated Temperatures," *Proc Inst Mech Engrs*, Trib Group Conv, Swansea, 1978, Paper 1.
- 29 Hollander, A. E., and Lancaster, J. K., "An Application of Topographical Analysis to the Wear of Polymers," *Wear*, Vol. 25, 1973, pp. 155-170.
- 30 Lancaster, J. K., "Accelerated Wear Testing of PTFE Composite Bearing Materials," *Tribology Int*, Vol. 12, 1979, pp. 65-75.
- 31 Evans, D. C., "The Influence of Abrasive Fillers on the Wear Properties of PTFE Composites," *Proc 2nd ASLE Int Conf on Solid Lub*, ASLE-SP-6, 1978, pp. 202-211.
- 32 Evans, D. C., Private communication.
- 33 Giltrow, J. P., and Lancaster, J. K., "Carbon Fibres in Tribology," *Proc 3rd Conf on Industrial Carbons and Graphites* London, 1970, *Soc Chem Ind*, pp. 483-490.
- 34 Thomas, T. R., "The Characterisation of Changes in Surface Topography During Running-In," *Proc 4th Leeds-Lyon Symposium on Surface Roughness Effects in Lubrication*, Lyon, 1977. In press.

DISCUSSION

B. D. McConnell¹

The authors have delved into the very interesting, but complex area of the mechanisms involved in self-lubricating bearing materials. These studies have generated additional data that leads to a greater understanding of the strengths and weaknesses of these type materials. The use of the powerful tools such as SEM, EDAX, and ESCA are providing the long needed link between friction and wear tests and the understanding of the fundamental mechanisms that govern the behavior of solid or dry lubricants. I can only urge them to continue these type studies with other dry lubricating materials to determine whether similar mechanisms and behavior are observed that may lay a sound, fundamental basis that all future applications can take advantage of.

Reading and studying this paper has generated some questions in my mind that hopefully the authors have already considered. If not, maybe they will stimulate further studies along these lines that may lead to new conclusions and greater understanding. First of all, the third body formation has been described as the transferring of material from the parent body (Liner) to the counterface and back to the liner surface, or simultaneously. Does this imply that film transfer in solid lubrication may be a self regulating, sacrificial wear process that quickly goes to an equilibrium or steady state? Does the increased concentration of the fluoride ion in the transferred film suggest that degradation of PTFE is necessary for successful lubrication? If so, could this analogy be applied to the lubrication by MoS₂ and the generation of sulfur ions in transfer films? And finally, do the authors feel the behavior found in these studies would be significantly different if less abrasive graphite fibers were substituted for the glass fibers and an inherently better lubricating resin, such as polyimide, was substituted for the phenolic? I would like commend the authors for initiating a very interesting study that has many implications for providing a greater understanding to one of the more intriguing areas of tribology.

¹ Air Force Materials Lab., Wright-Patterson AFB, Dayton, Ohio 45433.

Authors' Closure

We thank Mr. McConnell for his comments and questions on the paper, and would agree with his first point that film transfer does appear to be a self-regulating process which ultimately reaches an equilibrium condition. Whether or not this equilibrium is approached quickly, however, will depend on a number of factors, such as debris cohesion and adhesion, counterface roughness, etc; these are discussed more fully elsewhere [35]. Transfer must obviously occur in the first place from liner to counterface, but whether "back-transfer" is then possible is not known and, without the use of radio-tracer techniques, would be exceedingly difficult to prove.

The suggestion that degradation of PTFE might be a necessary requirement for successful lubrication does not seem to be wholly supported by the evidence presented in the Discussion section of the paper. Further, more recent, unpublished work by the authors has shown that transfer films produced from PTFE-fibre composites which do not incorporate glass fibre in the surface layer, contain greatly reduced amounts of F⁻. In the particular conditions of testing which were being used, the friction and wear properties of these composites were virtually identical to those containing glass fibre at the surface and producing F⁻-containing transfer films. Further work is clearly necessary to establish the precise role, if any, of PTFE degradation in solid lubrication.

We have no direct experimental information, as yet, on what would happen by replacing the glass fibre in the present, complex type of PTFE-fibre composite by graphite fibre. Certainly one would expect differences in friction and wear behaviour if only because the finely-divided degradation products from the graphite are likely to possess some lubricating ability in their own right. As a broad generalisation from previous work with bulk PTFE composites containing chopped fibres [36], it would appear that when using graphite fibres the counterface transfer films tend to be graphite-rich whereas when using

glass fibres the films are PTFE-rich. Such differences in composition would be expected to lead, for example, to differences in the environmental sensitivity of friction and wear and unpublished work has, in fact, shown that the wear resistance of PTFE/graphite fibre composites in vacuum is generally inferior to that of similar PTFE/glass composites. The precise part played by the abrasiveness of the fibres is not at all obvious at present and, indeed, it has always seemed somewhat surprising how little metal counterface damage is encountered in practice during the operation of woven PTFE fibre/glass

fibre types of dry bearings.

Additional References

- 35 Godet, M., Play, D. and Berthe, D. "An Attempt to Provide a Unified Treatment of Tribology Through Load Carrying Capacity, Transport and Continuum Mechanics," ASME Preprint 79-Lub-18.
- 36 Giltrow, J. P. and Lancaster, J. K. "The Friction and Wear of Carbon Fibre-Reinforced PTFE," *Proc AFML-MRI Conference on Solid Lubricants*, AFML-TR-70-127, 305-331, 1970.