

Heat Treatment of Gears

A Practical Guide for Engineers

A.K. Rakhit



Heat Treatment of Gears

A Practical Guide for Engineers

A.K. Rakhit



**The Materials
Information Society**

ASM International®
Materials Park, OH 44073-0002
www.asminternational.org

Copyright © 2000
by
ASM International®
All rights reserved

No part of this book may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the written permission of the copyright owner.

First printing, December 2000

Great care is taken in the compilation and production of this book, but it should be made clear that NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE GIVEN IN CONNECTION WITH THIS PUBLICATION. Although this information is believed to be accurate by ASM, ASM cannot guarantee that favorable results will be obtained from the use of this publication alone. This publication is intended for use by persons having technical skill, at their sole discretion and risk. Since the conditions of product or material use are outside of ASM's control, ASM assumes no liability or obligation in connection with any use of this information. No claim of any kind, whether as to products or information in this publication, and whether or not based on negligence, shall be greater in amount than the purchase price of this product or publication in respect of which damages are claimed. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF BUYER, AND IN NO EVENT SHALL EITHER PARTY BE LIABLE FOR SPECIAL, INDIRECT OR CONSEQUENTIAL DAMAGES WHETHER OR NOT CAUSED BY OR RESULTING FROM THE NEGLIGENCE OF SUCH PARTY. As with any material, evaluation of the material under end-use conditions prior to specification is essential. Therefore, specific testing under actual conditions is recommended.

Nothing contained in this book shall be construed as a grant of any right of manufacture, sale, use, or reproduction, in connection with any method, process, apparatus, product, composition, or system, whether or not covered by letters patent, copyright, or trademark, and nothing contained in this book shall be construed as a defense against any alleged infringement of letters patent, copyright, or trademark, or as a defense against liability for such infringement.

Comments, criticisms, and suggestions are invited, and should be forwarded to ASM International.

ASM International staff who worked on this project included Veronica Flint, Manager, Book Acquisitions; Bonnie Sanders, Manager, Production; Carol Terman, Copy Editor; Kathy Dragovich, Production Supervisor; and Scott Henry, Assistant Director, Reference Publications.

Library of Congress Cataloging-in-Publication Data

Rakhit, A.K.

Heat treatment of gears / A.K. Rakhit.

p. cm.

Includes bibliographical references and index.

1. Gearing—Heat Treatment. I. ASM International. II. Title.

TJ184.R35 2000 621.8'33—dc21 00-059341

ISBN: 0-87170-694-6

SAN: 204-7586

ASM International®
Materials Park, OH 44073-0002
www.asminternational.org

Printed in the United States of America

This book is dedicated to my parents, Mr. and Mrs. Upendra C. Rakhit; my wife, Ratna, for her understanding and inspiration; and my son, Amit, and daughter, Roma, for their love and support.

ASM International Technical Books Committee (1999–2000)

Sunniva R. Collins (Chair)
Swagelok/Nupro Company

Eugen Abramovici
Bombardier Aerospace (Canadair)

A.S. Brar
Seagate Technology Inc.

Ngai Mun Chow
Det Norske Veritas Pte Ltd.

Seetharama C. Deevi
Philip Morris, USA

Bradley J. Diak
Queen's University

James C. Foley
Ames Laboratory

Dov B. Goldman
Precision World Products

James F.R. Grochmal
Metallurgical Perspectives

Nguyen P. Hung
Nanyang Technological University

Serope Kalpakjian
Illinois Institute of Technology

Gordon Lippa
North Star Casteel

Jacques Masounave
Université du Québec

**Charles A. Parker, FASM (Vice
Chair)**
AlliedSignal Aircraft Landing
Systems

K. Bhanu Sankara Rao
Indira Gandhi Centre for Atomic
Research

Mel M. Schwartz
Sikorsky Aircraft Corporation
(retired)

Peter F. Timmins
University College of the Fraser
Valley

George F. Vander Voort
Buehler Ltd.

Contents

Preface	x
CHAPTER 1: Introduction to Gear Heat Treatment	1
CHAPTER 2: Properties of Iron	5
Alloys of Iron and Carbon	7
Transformation (Decomposition) of Austenite	10
CHAPTER 3: Heat Treatment of Gears	17
Major Heat Treat Processes	18
CHAPTER 4: Through-Hardening Gears	21
Through-Hardening Processes	22
Some Hints on Through-Hardened Gear Design	24
Hardness Measurement	25
Heat Treat Distortion of Through-Hardened Gears	25
Applications	26
Case History: Design and Manufacture of a Rack	27
Material Selection	27
Process Selection	29
CHAPTER 5: Carburizing and Hardening Gears	33
Gas Carburizing	34
Carburizing Temperature	34
Furnaces and Equipment for Gas Carburizing	36
Hardening	37
Direct Quenching	38
Reheating of Carburized Gears and Quenching	39
Surface Hardness Variations after Quenching	40
Tempering of Carburized and Quenched Gears	40
Recarburizing	42
Cold Treatment	43
Selection of Materials for Carburized Gears	44
Hardness and Hardenability	45
Carbon Content and Case Property	50
Core Hardness of Gear Teeth	62
Microstructure of Carburized Cases	68
Some Carburizing Problems	68

Heat Treat Distortion of Carburized and Hardened Gears	76
Mechanics of Heat Treat Distortion	77
Material and Heat Treat Process Factors	77
Vacuum-Melted versus Air-Melted Alloy Steels	81
Measurement of Gear Distortions	85
Some Recommendations to Minimize Distortion	86
Preheating of Gears	90
Distortion Characteristics of Some Gear Materials	90
Improvement in Gear Design to Control Heat Treat Distortion	91
Grinding Stock Allowance on Tooth Flanks to Compensate for Distortion	100
Grinding of Distorted Gears	101
Actual Stock Removal and Tooth Surface Hardness	103
New Pitting Life	105
Distortion Derating Factor	107
Side Effects of Grinding Carburized and Hardened Gears	108
Shot Peening of Carburized and Hardened Gears	111
Heat Treat Characteristics of Two Commonly Used Gear Materials: AISI 4320 and 9310	121
Carburizing Cost	122
Applications	123
Case History: Distortion Control of Carburized and Hardened Gears	123
New Heat Treat Facilities	124
Tests	125
Conclusions	131
CHAPTER 6: Nitriding Gears	133
Gas Nitriding Process	133
Recommended Tip and Edge Radii of Teeth	137
White Layer in Nitrided Gears	137
General Recommendations of Nitrided Gears	140
Microstructure of Nitrided Cases and Cores	141
Overload and Fatigue Damage of Nitrided Gears	143
Bending-Fatigue Life of Nitrided Gears	144
Nitriding Cost	145
Distortion in Nitriding	145
European Nitriding Steels	146
Applications	147
Case History A: Nitriding	148
Case History B: Failure of Nitrided Gears	152
CHAPTER 7: Modern Nitriding Processes	159
Ion/Plasma Nitriding Gears	159

Case History: Application of Ion Nitriding to an Internal Ring Gear at an Epicyclic Gear Box	164
CHAPTER 8: Carbonitriding Gears	171
Case Depth in Carbonitriding	172
Measurement of Case Depth	172
Materials	172
Distortion	172
Applications	173
CHAPTER 9: Induction Hardening Gears	175
Materials	176
Pre-Heat Treatment	176
Hardening Patterns	176
Heating with Induction	177
Quenching	178
Tempering	178
Surface Hardness and Case Depth	178
Induction Hardening Problems	180
Applications	182
Recent Advancements in Induction Hardening	182
Dual-Frequency Process	182
Flame Hardening	184
CHAPTER 10: Selection of Heat Treat Process for Optimum Gear Design	185
Materials Selection	185
Gear Design Feature	187
General Conclusions	188
CHAPTER 11: Selected References	189
Index	193

Preface

At the beginning of my career in gear design and manufacturing, I experienced a great deal of difficulty learning the art of gear heat treatment. I struggled a lot, attended a number of seminars on the subject, and spent a great deal of time experimenting with gear heat treatment. Over the last 50 years, a great deal of research has been carried out and published in the disciplines. Unfortunately, very little has been published on heat treatment of gears that is both easy to understand and useful to the gear engineer. This book has been specially written for the benefit of gear engineers engaged in design and manufacturing because I thought it would be beneficial to share my experience with the gear engineers of the future. I believe the information presented in this book will give them a good start in their careers.

Gears have been in existence for a long time. Before the invention of steel, gears were made of materials that were readily available and easily machinable, such as wood. Obviously, these gears did not last long and required frequent replacement. Cost was not as important as it is now.

Today there is continual demand for gear designs that transmit more power through smaller, lighter, quieter, and more reliable packages that must operate over a wide range of service conditions, with an increased emphasis on cost containment. The average life requirement for a gear in industrial service is now measured in millions of cycles. These requirements have accelerated the development and use of high-strength materials. Gears made of certain steels are found to meet these demands and to become especially effective when they are heat treated and finish machined for high geometric accuracy. This makes gear design and manufacturing more complex. In order to perform these tasks efficiently, a gear engineer needs to excel in various other disciplines besides design, such as manufacturing, lubrication, life and failure analysis, and machine dynamics.

Designing gears is a process of synthesis where gear size and geometry, materials, machining processes, and heat treatment are selected to meet the expected level of quality in the finished gears. These considerations are critical if the gears are to perform satisfactorily under anticipated service conditions. This led to the development of various design guidelines for an optimum gear set. However, in my opinion, the quality of gear heat treatment and its effect on gear performance and related cost are still not addressed.

In this book, I discuss gear heat treat distortion for the major heat processes in detail because my experience is that distortion of gears after heat treatment always presents difficulty in minimizing manufacturing cost. Hence, distortion control offers a challenging opportunity to a gear engineer not only in ensuring a high-quality product but also in controlling cost. A case history of each successful gear heat treat process is included. These case histories will provide important information on the quality of gear that can be expected with proper control of material and processes. This information will be beneficial not only in understanding distortion, but also in the selection of the proper gear material and appropriate heat treat process for a wide range of applications.

Writing a book takes a great deal of support and cooperation from many people. I wish to acknowledge all those who helped me with this project, with special thanks to Solar Turbines, Inc; to Mr. Bruce Kravitz of Kravitz Communications for proofreading and making many valuable editorial suggestions; and to Mrs. Sharon Jackson of Solar Turbines Inc., for typing the manuscript. I am also very grateful to Mr. Darle W. Dudley of Dudley Technical Group, Inc. for his guidance and encouragement with this project.

Finally, I would like to thank my many colleagues at the various gear manufacturing organizations with which I am associated for their help and inspiration.

A.K. Rakhit
June 2000

CHAPTER 1

Introduction to Gear Heat Treatment

MODERN GEARS are made from a wide variety of materials. Of all these, steel has the outstanding characteristics of high strength per unit volume and low cost per pound. These are the primary reasons that steel gears are used predominantly in industry today. Furthermore, the vast majority of gears made from either plain carbon or alloy steels is heat treated to increase strength and life. Although both plain carbon and alloy steels with equal hardness exhibit equal tensile strengths, alloy steels are preferred because of higher hardenability and the desired microstructures of the hardened case and core needed for high fatigue strength of gears. Over 90% of the gears used in industrial applications today are made from alloy steels. Hence, the scope of this guide is limited to the heat treatment of alloy steel gears.

Heat treatment of alloy steel gears is a complex process, and its scope lies from surface hardening to core treatment with proper control of both case and core microstructures. A well-controlled heat treatment produces the desirable surface and core properties for resistance to various failure modes. These failure modes include bending and contact (pitting) fatigues, and failures due to simple surface wear of gear teeth. The type of heat treatment used significantly affects metallurgical properties of the gears and the subsequent failure modes of the gears.

In addition to hardness and acceptable case/core microstructures, a gear design engineer expects gears to maintain pre-heat-treat tooth geometry after heat treatment, if possible. This allows gears to be finished with such minor operations as honing or lapping at acceptable quality and cost. But, unfortunately, the quality of gear geometry after heat treatment, carburizing in particular, deteriorates due to distortion to the extent that grinding of gear teeth becomes essential; the degree of distortion depends on the material, heat treat process, and equipment used. Although grinding can improve the geometry of gear teeth even with high distortion, this increases manufacturing cost significantly. Furthermore, ground gears

with high distortion may not perform satisfactorily due to the fact that grinding may remove the required case and lower the surface hardness of teeth. Thus, for optimal gear performance and reasonable manufacturing cost, it is essential that gear designers and manufacturing engineers have a good understanding of the various heat treatment processes that are used primarily for industrial and aerospace gears.

Of the various heat treating processes currently available, five are frequently used to heat treat alloy steel gears. These processes are through hardening, case carburizing and hardening, nitriding, carbonitriding, and induction hardening. Analyses of these processes show case carburizing and hardening offers the highest torque-carrying capacity of gears. In fact, the torque capacity of a carburized and hardened gear set can be three to four times higher than that of a similar through-hardened gear set. It is also significantly higher than a nitrided or an induction-hardened set. For this reason, case carburized and hardened gears are extensively used in industrial, automotive, and aerospace applications. Nitriding process is used primarily because of low distortion and in applications where gears are not heavily stressed and do not require high case depths, for which nitriding is not cost effective. High case depths often produce unacceptable microstructures of the nitrided case detrimental to gear life.

Until recently, carburized and ground gears were not considered economical because of high finishing cost. This concept was based on some inefficient carburizing equipment and processes. With the recent development of improved heat treat equipment and some high-quality carburizing grade steels, it is now possible to control and predict heat treat distortion during carburizing and quenching to the extent that grinding time is significantly reduced. In some cases, minor modifications of pre-heat treat gear-cutting tools (hobs, shaper cutters) help to compensate heat treat distortion that reduce grind time even further. Also, carburized and hardened gear sizes are smaller compared with those heat treated by other processes for the same horsepower (hp) because of higher allowable stresses in design. This results in smaller gear units with lower cost/hp and shorter center distances between the gears. Hence, the use of carburized gears is increasing continually.

In spite of the fact that more gears are being carburized than in the past, the process is not yet fully understood from a distortion point of view. A large number of heat treating organizations still regard the process as a black art. These manufacturers forget that case carburizing, like any other manufacturing process, is very much a scientific process. The problems associated with this process are easily identifiable with proper explanation. This book has been specially prepared for this purpose. It is expected to provide a better understanding of the carburizing process to gear engineers. In this regard, problems associated with commonly used gear materials such as American Iron and Steel Institute (AISI) 8620 and AISI 9310 are discussed. Also discussed are problems with high-alloy steels

such as AISI 4330 and HP 9-4-30 that are used extensively in the aerospace industry. In many of these applications, even with high material cost per pound, an optimal design is achieved with gears made from these steels. This is due largely to controllable heat treat distortion of these materials that helps to reduce gear finishing cost.

To appreciate the advantages of the carburizing process, other heat processes such as through hardening, nitriding, carbonitriding, and induction hardening also are discussed, especially the limitations of these processes to optimal gear design. The distortion in the nitriding process, sometimes considered an alternative to carburizing, is comparatively less but cannot be ignored, particularly when conventional gas nitriding is used. For example, the quality of gas-nitrided gears may drop from American Gear Manufacturers Association (AGMA) class 10 to class 9 after nitriding, whereas the quality of similar carburized gears may go down to AGMA class 8. From the last decade to date, the use of through-hardened gears has been reduced significantly. On the other hand, induction hardening, particularly the dual frequency method, sometimes provides an alternative to carburizing and nitriding for large-sized gears.

As already mentioned, minor modification of pre-heat treat cutting tools designed to accommodate the expected distortion minimizes finishing operation and thus, gear cost. But this is possible only with known and consistent distortion of gears. Unfortunately, distortion characteristics of gears for various heat treat processes and materials are not easily available. For an optimal design, therefore, it is imperative that both design and manufacturing engineers become familiar with the various gear heat treat processes and understand the mechanism of heat treat distortion, for which some knowledge of the properties of iron (the basic ingredient of steel), iron-carbon phase diagram, and the properties of some common alloying elements is considered helpful.

Chapter 11: Selected References

Technical Papers

- J.O. Almen, Peened Surfaces Improve Endurance of Machine Parts, *Met. Prog.*, Feb 1943, p 9–15
- R.A. DePaul, High Cycle and Impact Fatigue Behavior of Some Carburized Gear Steels, *Met. Eng. Q.*, Nov 1970 doi: [10.4271/710277](https://doi.org/10.4271/710277)
- R. Drago, “An Improvement in the Conventional Analysis of Gear Tooth Bending Fatigue Strength,” *Fall Technical Meeting*, American Gear Manufacturers Association, 1982
- D.W. Dudley, “How Increased Hardness Reduces the Size of Gear Sets,” *Prod. Eng.*, Nov 1964
- D.W. Dudley, “Load Rating Practices of Carburized and Nitrided Gears,” *presented at the 10th Round Table Conference on Marine Gearing*, Brunnen, Switzerland, 25–26 Sept 1975
- J.R. Eagan and C.H. Shelton, “Recent Test Data on Selection of Alloy Steels for Gears and Bearings,” *Society of Automotive Engineers (SAE) Report 720301*, 1972 doi: [10.4271/720301](https://doi.org/10.4271/720301)
- H. Fugio and T. Aida, “Study on Gear Distortion Caused by Hardening,” *ASME Paper 80-C2/DET-51*, American Society of Mechanical Engineers, 1980
- K. Fujita and A. Yoshida, Surface Durability of Steel Rollers, (Case-Hardened and Nitrided), *Bull. JSME*, Vol 21 (No. 154), April 1978 doi: [10.1299/jsme1958.21.761](https://doi.org/10.1299/jsme1958.21.761)
- R.C. Graham, A. Oliver, and P.B. Macpherson, “An Investigation into the Mechanisms of Pitting in High-Hardness Carburized Steels,” *ASME Paper 80-C2/DET-118*, American Society of Mechanical Engineers, 1980
- F.E. Harris, Case Depth—An Attempt at a Practical Definition, *Met. Prog.*, Vol 44 (No. 2), p 265–272, 1943
- W.J. Harris, The Influence of Shot Peening on the Fatigue Properties of Steel, *Metallurgia*, Vol 45 (No. 272), June 1952
- J.M. Heberling, “Engineering Report on Hardenability of Gear Steels,” Allied Signal Aerospace Company, Torrance, CA, 1989
- H.M. Hiersig, “Capacity Limits of the Largest Pairs of Carburized Gears to be Produced with Available Equipment,” *ASME Paper 84-DET-84*, American Society of Mechanical Engineers, 1984

- B. Hildenwall and T. Ericsson, *Hardenability Concepts with Application to Steel*, The Metallurgical Society AIME, New York, 1978, p 579
- M. Hirt and H. Weiss, “Increase of Load Capacity by Use of Large Case-Hardened Gears,” *Fall Technical Meeting*, American Gear Manufacturers Association, 1981
- M.A.H. Howes and J.P. Sheehan, “The Effect of Composition and Microstructure on the Pitting Fatigue of Carburized Steel Cases,” *Paper 740222*, Society of Automotive Engineers, 1974 doi: [10.4271/740222](https://doi.org/10.4271/740222)
- A. Ishibashi and S. Tanaka, “Appreciable Increase in Pitting Limit of a Through-Hardened Steel,” *ASME Paper 80-2/DET-28*, American Society of Mechanical Engineers, 1980
- R.F. Kern, Selecting Steels for Carburized Gears, *Met. Prog.*, July 1972, p 53–64
- H.O. Kron, “Gear Tooth Sub-Surface Stress Analysis,” *Congres Mondial des Engrenages, Paper A10*, 1977
- F.T. Krotine, M.F. McGuire, and A.R. Troiano, The Influence of Case Properties and Retained Austenite on the Behavior of Carburized Components, *Trans. ASM*, Vol 62 (No. 4), 1969, p 829–839
- W.L. McIntire, R.C. Malott, and T.A. Lyon, “Bending Strength of Spur and Helical Gear Teeth,” *Fall Technical Meeting*, American Gear Manufacturers Association, 1967
- M.A. Miner, Cumulative Damage in Fatigue, *J. Appl. Mech.*, Vol 12, 1945 doi: [10.1115/1.4009458](https://doi.org/10.1115/1.4009458)
- S. Oda, Y. Shimatomi, and K. Nobuyuki, “Study on Bending Fatigue Strength of Helical Gears,” *Bull. JSME*, Vol 23 (No. 177), Paper 117-17, 1980 doi: [10.1299/jsme1958.23.461](https://doi.org/10.1299/jsme1958.23.461)
- R. Pederson and R.L. Rice, Case Crushing of Carburized and Hardened Gears, *Trans. SAE*, 1964, p 250
- G.W. Powell, M.B. Benet, and C.F. Floe, Carbonitriding of Plain Carbon and Boron Steels, *Trans. ASM*, Vol 46, 1954, p 1359–1371
- A.K. Rakhit, “Distortion Control of Carburized and Hardened Gears,” *ASME Paper 84-DET-224*, American Society of Mechanical Engineers, 1984
- A.K. Rakhit, “Optimization of Case Depth and Core Hardness for Carburized and Hardened High Alloy Steel Gears,” *Engineering Report ME89-145 AKR*, Allied Signal Aerospace, Torrance, CA, 1989
- A.K. Rakhit, “Effect of Uncontrolled Heat Treat Distortion on the Pitting Life of Ground, Carburized and Hardened Gears,” *Paper 98FTM4*, presented at the AGMA Fall Technical

Meeting (Cincinnati, OH), American Gear Manufacturers Association, 1998 doi: [10.1115/DETC98/PTG-5787](https://doi.org/10.1115/DETC98/PTG-5787)

- C. Razim, Influence of Residual Austenite on the Strength of Case-Hardened Specimens under Conditions of Fluctuating Stress, *Hart.-Tech. Mitt.*, Vol 23, 1968, p 1–8
- V.S. Sagaradze, Effect of Heat Treatment on the Properties of High Carbon Alloyed Steels, *Met. Sci. Heat Treat.*, No. 12, 1964, p 720 doi: [10.1007/BF00660227](https://doi.org/10.1007/BF00660227)
- V.K. Sharma, G.H. Walter, and D.H. Breen, “An Analytical Approach for Establishing Case Depth Requirements in Carburized Gears,” *ASME Paper 77-DET-152*, American Society of Mechanical Engineers, 1977
- J.P. Sheehan and M.A.H. Howes, “The Role of Surface Finish in Pitting Fatigue of Carburized Steels,” *Paper 73058*, Society of Automotive Engineers, 1973 doi: [10.4271/730580](https://doi.org/10.4271/730580)
- D.P. Townsend and E.V. Zaretsky, “Effect of Shot Peening on Surface Fatigue Life of Carburized and Hardened AISI 9310 Spur Gears,” *NASA Report TP-2047*, NASA Lewis Research Center, Cleveland, OH, 1982
- D.P. Townsend, “Improvement in Surface Fatigue Life of Hardened Gears by High-Intensity Shot Peening,” *NASA AVSCOM Technical Report 91-C-042*, NASA Lewis Research Center, Cleveland, OH, 1992 doi: [10.1115/DETC1992-0082](https://doi.org/10.1115/DETC1992-0082)
- T. Ueno, Y. Ariura, and T. Nakanishi, “Surface Durability of Case Carburized Gears: On a Phenomenon of ‘Gray-Staining’ of Tooth Surface,” *ASME Paper 80-C2/DET-27*, American Society of Mechanical Engineers, 1980
- F. Vodopivec and L. Kosec, The Fatigue Strength and Influence of Non-Metallic Inclusions on the Fatigue Fracture of Case Hardening Steels, *Hart.-Tech. Mitt.*, Vol 22, 1967, p 166

Books

- *Carburizing and Carbonitriding*, American Society for Metals, 1977
- “Design Engineering Specification for Gears,” *ES 9-45*, Solar Turbines, Inc., San Diego, CA
- T.G. Diggs, S.J. Rosenberg, and G.W. Geil, *Heat Treatment and Properties of Iron and Steel*, National Bureau of Standards Monograph 88, 1966 doi: [10.6028/NBS.MONO.88](https://doi.org/10.6028/NBS.MONO.88)
- D.W. Dudley, *Gear Handbook*, McGraw-Hill Book Company, Inc., 1962
- D.W. Dudley, *Handbook of Practical Gear Design*, Technomic Publishing Co., Inc., 1994
- D.W. Dudley and H. Winter, *Gears*, Springer-Verlag, Berlin, 1961, in German

- “Fundamental Rating Factors and Calculation Methods for Involute Spur and Helical Gear Teeth,” *ANSI/AGMA 2001-C95*, American Gear Manufacturers Association, 1995
- “Gear Materials and Heat Treatment Manual,” 2004-B89, American Gear Manufacturers Association, 1989
- “Ion Nitriding,” *AMS 2759/8*, Society of Automotive Engineers (SAE) Aerospace Material Specification, 1992
- *Manual of Shot Peening Technology*, Wheelabrator Frye, Inc., Mishawaka, IN, 1977
- *Nitralloy and the Nitriding Process*, The Nitralloy Corporation, New York, 1954
- *Nitreg Nitriding Technology*, Nitrex Metal, Inc., Canada, 1991
- *Plasma-Triding*, Metal Plasma Technology, Valencia, CA
- “Recommended Practice for Carburized Aerospace Gearing,” 926-C99, American Gear Manufacturers Association, 1999
- *Republic Alloy Steels*, Republic Steel Corporation, Cleveland, OH, 1961
- *Shot Peening Applications*, 6th ed., Metal Improvement Company, Paramus, NJ, 1980
- C.A. Siebert, D.V. Doane, and D.H. Breen, *The Hardenability of Steels: Concepts, Metallurgical Influences, and Industrial Applications*, American Society for Metals, 1977
- “Surface Temper Inspection Process,” 230.01, American Gear Manufacturers Association, 1968
- D.P. Townsend, Ed., *Dudley’s Gear Handbook: The Design, Manufacture and Application of Gears*, 2nd ed., McGraw-Hill Inc., New York, 1991