

## Removal of cadmium ion from wastewater by carbon-based nanosorbents: a review

Rajeev Kumar, Jyoti Chawla and Inderpreet Kaur

### ABSTRACT

A green environment and a healthy life are dream projects of today's science and technology to save the world. Heavy metal ions in water affect both environment and human health. Cadmium has been identified as one of the heavy metals that causes acute or chronic toxic effects if ingested. Increasing use of cadmium in different technological fields has raised concern about its presence and removal from water/wastewater. Researchers have made many systematic efforts to remove heavy metals from water to reduce their impact on human beings and the environment. Adsorption is one of the best methods to remove heavy metals from water among the different proposed methods. This study explores carbon-based nanosorbents which have been proved as effective adsorbents for removal of cadmium ions from water. The adsorption efficiency of carbon-based nanosorbents is the main criterion to rank and select them for removal of cadmium ions from water. Toxicity, reusability and environmentally friendly characteristics of sorbents are also taken considered while ranking the suitable carbon-based nanosorbents for removal of cadmium ions from water.

**Key words** | cadmium poisoning, cadmium removal, carbon-based nanosorbents, nanomaterials, purification, water pollution

**Rajeev Kumar** (corresponding author)  
**Jyoti Chawla**  
Department of Chemistry,  
Manav Rachna International University,  
Faridabad,  
India  
E-mail: rajeevkumar.fet@mriu.edu.in

**Inderpreet Kaur**  
Department of Chemistry,  
Guru Nanak Dev University,  
Amritsar,  
India

### INTRODUCTION

Natural waters are mostly polluted by heavy metal ions caused by industrial wastage. Due to their toxic effects metal ions pose a serious threat to living organisms (Khan *et al.* 2008; Singh *et al.* 2010; Zhao *et al.* 2011a, b) and the environment in terms of growth, yield and quality of crops and plants (Singh & Agrawal 2010; Ok *et al.* 2011). Mercury, cadmium, arsenic, chromium and lead have the most serious effects on human beings as well as on the environment. Cadmium is of toxicological concern because of its bioaccumulation and non-biodegradability property even at very low concentration (Waalkes 2000; Li *et al.* 2012; Amin *et al.* 2013). Cadmium is widely used in making nickel-cadmium batteries, pigments, phosphate fertilizers, alloys and metal plating (John & Santhi 1994; Mhiaoui *et al.* 2003; Lambert *et al.* 2007; Martinis *et al.* 2009). Runoff from waste batteries and paints, corrosion of galvanized pipes and discharge from metal refineries are identified sources of cadmium exposure in water (Hutton

& Symon 1986; Akesson 2011). Cadmium may be introduced into water naturally by volcanic eruption. The typical permissible cadmium concentration as per the WHO (2008) and EPA (2008) guidelines in drinking water is 0.003 mg/L and 0.005 mg/L, respectively. High concentration of cadmium above the recommended value in water causes serious poisoning in human beings.

Many research groups have focused their interest on removal of heavy metal ions from water/wastewater. A number of methods have been developed to remove heavy metal ions from water, such as ion exchange, reverse osmosis, precipitation, cementation and adsorption (Charerntanyarak 1999; Dabrowski *et al.* 2004; Qdais & Moussa 2004; Hua *et al.* 2012). Among them, adsorption is considered as an effective, efficient and economic method (Sud *et al.* 2008; Lo *et al.* 2012). Among the various traditional adsorbents for water purification, nanosorbents have emerged with great potential and accuracy because of their high surface area

doi: 10.2166/wh.2014.024

and high efficiency. Nanosized metal oxide, nanocomposites, magnetic nanoparticles and carbon nanotubes have been most effectively used and extensively reviewed for removal of heavy metals from water (Ngomsik *et al.* 2005; Wang *et al.* 2010; Zhao *et al.* 2011a, b; Hua *et al.* 2012; Kumar & Chawla 2014). However, removal of cadmium metal ions by different nanomaterials needs to be studied in greater detail to explore their toxicity, reusability, cost, and maximum efficiency.

This review provides an overview of carbon-based nanosorbents for removal of cadmium from water with the challenge of the environmental impacts, regeneration and reusability characteristics of these nanosorbents. The review is divided into the following sections:

- Cadmium poisoning and health effects
- Nanosorbents for removal of heavy metals from water
- Review of carbon-based nanosorbents for removal of cadmium
- Result analyses
- Conclusions.

---

## CADMIUM POISONING AND HEALTH EFFECTS

Cadmium poisoning is associated with various clinical complications in human beings. Cadmium is a well-known nephrotoxic agent (Wu *et al.* 2008). Cadmium has a very long biological half-time of 10–30 years in humans (Swaddiwudhipong *et al.* 2012) and accumulates primarily in kidney cells with development of chronic disease. The accumulation of cadmium in the kidney leads to dysfunction of the kidney. The ingestion of cadmium in human beings poses a great health risk even at very low concentrations (Waalkes 2003). Kidney damage and lung emphysema are the primary effects of high exposure of cadmium in the body. However, the other target organs that may be affected by the accumulation of cadmium in the body are liver, intestines, placenta, pancreas, heart, skeletal system, immune systems, reproductive system and nervous system (Fowler 2009; Ciarrocca *et al.* 2013). Cadmium poisoning sometimes causes hypertension, diabetes, nerve or brain damage, liver disease and urinary stones (Horiguchi *et al.* 2004; Fowler 2009). Cadmium poisoning may also cause bone damage

(Jarup & Akesson 2009) and affects teeth and the nervous system permanently by replacing calcium. Long-term exposure to cadmium and excessive intake of cadmium causes serious illnesses such as itai-itai disease in human beings (Bolan *et al.* 2013). In addition, recently cadmium has been identified as a human carcinogen; increasing concentrations of cadmium in water increases cancer risk in humans (Mahalik *et al.* 1995; Fowler 2009).

---

## NANOSORBENTS FOR REMOVAL OF HEAVY METALS FROM WATER

Toxic heavy metal ions removal from water/wastewater by using synthetic compounds, polymers and other materials as sorbents is of great concern in environmental research applications (Moradi *et al.* 2009; Fu & Wang 2011). A number of traditional sorbents have been used for removal of cadmium from water/wastewater. Agricultural waste materials such as stems (Tan & Xiao 2009), husks (Panda *et al.* 2006), bark (Ghodbane *et al.* 2007), shell (Cimino *et al.* 2000), peels (Li *et al.* 2007), leaves (Sharma & Bhattacharyya 2005) and saw dust (Memon *et al.* 2007) have been extensively used as traditional sorbents for removal of cadmium. However, the use of traditional sorbents has been restricted by the inconvenience of separation in multi-metal ions solution, poor performance and efficiency. Over the last decade nanomaterials have been extensively studied for their potential applications in various applied fields, such as energy application, quantum dots for biomedical application, and photocatalytic applications (Krishna *et al.* 2013; Han & Ho 2014; Lee & Jang 2014). The sorption potential of nanomaterials has not been studied extensively. Nanomaterials are a promising material in terms of separation, performance and efficiency for removal of heavy metals from water because of their unique properties, such as small size, high specific surface area and morphological features (Hua *et al.* 2012). Nanomaterials have been found to be superior sorbents for various organic and inorganic pollutants, such as benzene (Gauden *et al.* 2006), fluoride and ethidium bromide (Li *et al.* 2003c; Najafi *et al.* 2013). The synthetic method of nanomaterials has been intensively developed and designed not only for their fundamental scientific interest but also their important application in

sorption fields in order to get maximum efficiency (Shamsudin *et al.* 2013). The sorption capacity of nanomaterials was found to be improved by oxidation, modification or functionalization on the surface of nanomaterials (Khani & Moradi 2013). The European Commission on 18 October 2011 adopted the definition of a nanomaterial as a natural, incidental or manufactured material containing particles, in an unbound state or as an aggregate or as an agglomerate and where, for 50% or more of the particles in the number size distribution, one or more external dimensions are in the size range 1–100 nm. In specific cases and where warranted by concerns for the environment, health, safety or competitiveness the number size distribution threshold of 50% may be replaced by a threshold between 1 and 50%. A number of carbon-based nanoparticles, nanometal oxides, magnetic nanoparticles, nanocomposites, dendrimers, zeolites, nanoclays and modifications of functionalized nanomaterials have been widely used as adsorbent to remove heavy metal ions from water or wastewater (Hu *et al.* 2006; Ghorbani & Eisazadeh 2013).

## REVIEW OF CARBON-BASED NANOSORBENTS FOR REMOVAL OF CADMIUM

Carbon-based nanomaterials include carbon nanotubes, oxidized carbon nanotubes, carbon-based fibres, graphene, carbon nanocomposites and fullerene. Raw carbon-based nanomaterials and modified carbon-based nanomaterials have been extensively used for removal of heavy metal ions from water. The following section describes the detailed study of carbon-based nanomaterials used as nanosorbent for removal of cadmium ions from water/wastewater.

### Carbon nanotubes

The study of adsorption properties of carbon nanotubes (CNTs) plays an important role in the advance of research and technology for water purification. The applications of CNTs for the removal of heavy metal ions from aqueous systems have been extensively studied because of their large specific surface area (3,000 m<sup>2</sup>/g), mechanical stability and highly porous structure (Yin *et al.* 1999; Sheikh 2008; Moradi *et al.* 2012). Heavy metal ion adsorption capacity of

CNTs is directly related to their total active surface acidity. Generally, CNTs can be synthesized by electric arc discharge, pulse laser vapour and catalytic decomposition of gaseous hydrocarbons (Ando *et al.* 2004; Balasubramanian & Burghard 2005). CNTs synthesized by two-stage catalytic chemical vapour deposition (CVD) method gives the highest aspect ratio, renders the lowest integrated intensity ratio and diameter size distribution, and provides excellent purity of CNTs (Shamsudin *et al.* 2013). Defects on the walls of CNTs decrease their adsorbent capacity. The sorption capacity of Cd<sup>2+</sup> ion onto 10 mg of CNTs dosage of the average diameters in the range of 20–30 nm and 0.789 mg/L initial concentration observed was 19.14% at pH 7.0 for 120 minutes of contact time (Kabbashi *et al.* 2011). On the other hand, CNTs were grown on the surface of micro-sized Al<sub>2</sub>O<sub>3</sub> particles for removal of Cd<sup>2+</sup> and other heavy metal ions from aqueous solutions (Hsieh & Horng 2007). The adsorption capacity of CNTs grown on Al<sub>2</sub>O<sub>3</sub> was superior to that of active carbon powders, commercial carbon nanotubes and Al<sub>2</sub>O<sub>3</sub> particles. Although the adsorption capacity of Cd<sup>2+</sup> ion on CNTs grown on Al<sub>2</sub>O<sub>3</sub> was lower than the Pb<sup>2+</sup> and Cu<sup>2+</sup> ions, it could be increased by further treatment or oxidation. The calculated saturation amount for Cd<sup>2+</sup> was 2.0, 6.19 and 8.89 mg/g, adsorbed by 1 g of Al<sub>2</sub>O<sub>3</sub>, commercial CNTs and CNTs grown on Al<sub>2</sub>O<sub>3</sub> respectively.

Different oxidizing reagents such as HNO<sub>3</sub>, H<sub>2</sub>O<sub>2</sub> and KMnO<sub>4</sub> were used for oxidation of CNTs (Khani & Moradi 2013). Oxidized CNTs show exceptionally high adsorption capacity and efficiency for removal of heavy metal ions. Enhancement in the adsorption capacity and efficiency of oxidized CNTs is explained due to incorporation of the oxygen containing functional groups on the surface of CNTs by chemical oxidation. Carboxylic and phenolic groups present on the carbon surface exhibit high affinity for various metal ions in water (Kadirvelu & Namasivayam 2003). Langmuir maximum adsorption capacity of Cd<sup>2+</sup> ion onto oxidized carbon nanotube was higher than other metal ions such as Co<sup>2+</sup>, Zn<sup>2+</sup>, and Cu<sup>2+</sup> (Gao *et al.* 2009; Tofighy & Mohammadi 2011). The adsorption efficiency of oxidized CNTs for cadmium and other metal ions has also been investigated in single, binary, ternary and quaternary systems (Gao *et al.* 2009). The amount of Cd<sup>2+</sup> ions adsorbed on the oxidized CNTs was higher than

the  $\text{Zn}^{2+}$  for single and binary systems. However, the adsorption process became more and more complicated for ternary and quaternary systems and showed a different order. Ion exchange or outer-sphere surface mechanism was suggested to be predominant over the complex mechanism of the removal process. However, ion exchange or outer surface mechanism mainly contributes to  $\text{Cd}^{2+}$  uptake on oxidized multi-walled carbon nanotubes (MWCNTs) at low pH and inner-sphere surface mechanism is the main uptake mechanism at high pH values (Yang *et al.* 2012). The effect of different oxidizing reagent on carbon nanotubes was also investigated to find out the maximum adsorption capacity of  $\text{Cd}^{2+}$  ion from aqueous solution. Three oxidizing reagents,  $\text{H}_2\text{O}_2$ ,  $\text{KMnO}_4$  and  $\text{HNO}_3$ , have been used to compare the adsorption efficiency of oxidized CNTs (Li *et al.* 2003b). As compared to CNTs,  $\text{KMnO}_4$  oxidized CNTs showed high absorption capacity. The adsorption capacity of  $\text{Cd}^{2+}$  on CNTs was only 1.1 mg/g at a 4 mg/L  $\text{Cd}^{2+}$  ion equilibrium concentration while it reached 2.6, 5.1 and 11.0 mg/g for the  $\text{H}_2\text{O}_2$ ,  $\text{HNO}_3$  and  $\text{KMnO}_4$  oxidized CNTs, respectively, at the same concentration. Adsorption capacities for three types of oxidized CNTs were greater because oxidation of CNTs introduces functional groups on the surface and increases the surface area. The specific surface area of  $\text{H}_2\text{O}_2$ ,  $\text{KMnO}_4$  and  $\text{HNO}_3$  oxidized carbon nanotubes was found to increase from 122 to 130, 128 and 154  $\text{m}^2/\text{g}$ , respectively, by the oxidation process. The adsorption capacity of  $\text{Cd}^{2+}$  for  $\text{KMnO}_4$  oxidized CNTs was sharply increased with increasing the dosage of CNT because host manganese residuals on oxidized CNTs surface by  $\text{KMnO}_4$  contribute to cadmium sorption. Furthermore, the adsorption capacities and efficiency of cadmium ion also depend on the type of CNTs, i.e., single-walled carbon nanotubes (SWCNTs) and MWCNTs.

Single-walled carbon nanotubes are composed of a single rolled-up graphene sheet and MWCNTs are composed of a concentric arrangement of many cylinders. In a graphite arc process that forms fullerenes from atomized carbon, multi-walled CNTs are deposited at the graphite anode (Iijima 1991). Single-walled carbon nanotubes were also synthesized in the presence of metal catalyst (Iijima & Ichihashi 1993). Limited work has been done on the removal of cadmium ion by SWCNTs and modified

SWCNTs. The removal efficiency of  $\text{Cd}^{2+}$  ions by SWCNTs has been investigated in detail only by Moradi (Moradi *et al.* 2010, 2011; Moradi 2011; Moradi & Zare 2011). Langmuir maximum adsorption capacity of  $\text{Cd}^{2+}$  ion observed was 24.07 mg/g on SWCNT at pH 5.0–6.0. The degree of sorption with respect to temperature on the sorbent surface has been explained on the basis of thermodynamic parameters, such as change in free energy ( $\Delta G$ ), change in enthalpy ( $\Delta H$ ) and change in entropy ( $\Delta S$ ). The negative value of free energy of adsorption indicates the feasibility of the process. However, a negative value of enthalpy of adsorption shows an exothermic process and a positive value of enthalpy of adsorption shows an endothermic process. The positive value of entropy of adsorption indicated spontaneous sorption process with high affinity (Tadjarodi *et al.* 2013). Thermodynamic parameters values showed that the adsorption process of ions was taking place by physisorption on the surface of SWCNTs and was spontaneous and endothermic in nature at 283–313 °K (Moradi *et al.* 2010, 2011).

Multi-walled carbon nanotubes are formed by two or more rolled-up graphite sheets. The available adsorption space is either external surface or inter-wall spaces, i.e., the spaces between the coaxial tubes of MWCNTs (Yang & Xing 2007). Three carbon-based materials including MWCNTs (5–10 nm), activated carbon (AC) and carbon encapsulated magnetic nanoparticles (CEMNPs) (40–90 nm) were used for the comparative study of cadmium adsorption under similar conditions (Pyrzynska 2010). The results showed that the theoretical saturation capacity for cadmium was 9.91, 20.37 and 91.0 mg/g for AC, CNTs and CEMNPs, respectively, at pH 8.0. High adsorption capacity of CEMNPs towards cadmium ions was explained by the synergistic effect between CNTs and iron oxides which improves the affinity of the adsorbent. The results indicate that specific active sites on the sorbents play an important role in metal ions' retention. There was competition among the different heavy metal ions for binding of the active sites present on the MWCNTs' surface. However, it was found that  $\text{Cd}^{2+}$  ion has slightly low affinity for binding of the active sites present on the MWCNTs' surface compared to other metal ions such as  $\text{Cu}^{2+}$ ,  $\text{Zn}^{2+}$  and  $\text{Pb}^{2+}$  (Li *et al.* 2003a; Salam *et al.* 2012). The spontaneity of the adsorption process was confirmed by the calculated

thermodynamics parameters (Salam 2013). Calculated thermodynamics parameters showed that the value of the free energy was negative while the change in entropy value was positive for cadmium ions. Positive value of entropy is due to the physical adsorption of cadmium ions from the aqueous solution to the surface of carbon nanotubes which increases randomness on the surface.

### Modified carbon nanotubes

Modification on the surface plays an important role in increasing the sorption capacity of CNTs. It was found that amines with oxygen containing groups on the surface might be coordinating sites for sorption of heavy metal ions (Vukovic *et al.* 2011; Wang *et al.* 2013). The surface modification of CNTs can be done either by chemical bond formation or by physical adsorption (Wildgoose *et al.* 2006). Nanotubes are slightly less stable in polar solvents and tend to aggregate in solution. Surface modification also helps in stabilizing the dispersion in solvents and imparts high stability in solution. Both SWCNTs and MWCNTs were modified with different groups to increase the sorption capacity of CNTs for removal of heavy metals. The adsorption properties of carbon nanotubes were significantly improved by modification with different groups for removal of cadmium metal ions. Different parameters such as effects of temperature, pH, ionic strength, metal ion concentration and the amount of modified CNTs were studied for adsorption of heavy metal ions from water. The interaction of cadmium metal ions with carboxylate group functionalized single-walled carbon nanotube (SWCNT-COOH) surface was found to be higher than the single-walled carbon nanotube (SWCNT) surface due to the carboxyl group which increases negative charge on carbon nanotube surface (Moradi *et al.* 2011). Also, surface functionalization improved their stability in water and adsorption efficiency towards heavy metal ions (Li *et al.* 2003a; Feng *et al.* 2008). Langmuir maximum adsorption capacity of  $\text{Cd}^{2+}$  ion was increased from 24.07 to 55.89 mg/g on SWCNT-COOH at pH 5.0–6.0. Thermodynamic parameter values showed that adsorption processes of ions was taking place by chemisorption on the surface of SWCNTs-COOH and physisorption on the surface of SWCNTs and were spontaneous and endothermic

in nature at 283–313 °K (Moradi *et al.* 2010, 2011; Moradi 2011; Moradi & Zare 2011).

The adsorption properties of MWCNTs were significantly improved by modified multi-walled carbon nanotubes with different groups such as six-arm amino polyethylene glycol (PEG), 8-hydroxyquinoline, ethylenediamine (En) (Vukovic *et al.* 2010; Kosa *et al.* 2012; Salam 2013; Velickovic *et al.* 2013). The maximum adsorption capacities of  $\text{Cd}^{2+}$  ions on the surface of modified MWCNTs by six-arm amino PEG (MWCNTs-PEG) was 77.6 mg/g for initial cadmium ion concentration of 10 mg/L at pH 8.0 (Velickovic *et al.* 2013). Minimum adsorption was observed at lower pH because at lower pH high concentration of hydrogen ions are present and, according to surface complex formation theory, hydrogen ions are preferentially adsorbed rather than the metal ions (Kosa *et al.* 2012). The percentage adsorption of  $\text{Cd}^{2+}$  ions increased from 14.3 to 61.7% by MWCNTs and from 40.67 to 100% by modified multi-walled carbon nanotubes when pH increases from 6.0 to 9.0 because cadmium usually precipitates at higher pH values (Lv *et al.* 2005). Intra-particle Weber–Morris kinetic model was used to describe the time-dependent adsorption. The initial adsorption reached equilibrium gradually at 97% of cadmium adsorption by physisorption process.

The MWCNTs with very few oxygen containing functional groups showed relatively low sorption capacities for  $\text{Cd}^{2+}$  (Tian *et al.* 2012). The sorption capacity of  $\text{Cd}^{2+}$  ions by MWCNTs was increased by surface coating with manganese dioxide ( $\text{MnO}_2$ ), (MWCNTs- $\text{MnO}_2$ ) or with humic acids (Yang *et al.* 2011; Tian *et al.* 2012; Luo *et al.* 2013). Surface coating with four sequentially extracted humic acids on three multi-walled CNTs (MWCNTs) with different surface areas affected the adsorption process of heavy metal ions significantly. However, surface coating with the humic acids lowered the surface areas of the MWCNTs but greatly increased their sorption capacities because of complexation and electrostatic attraction (Tian *et al.* 2012). Surface coating with the humic acids introduced oxygen containing functional groups and increased negative charge on the MWCNTs' surface. The adsorption efficiency of multi-walled carbon nanotubes for the removal of heavy metal ions could also be increased by modification with chitosan (Salam *et al.* 2011). Two real water samples were collected


from the Red Sea and a wastewater treatment plant to evaluate the applicability of the nanosorbent (Kosa *et al.* 2012). Most of the metal ions were removed from the solution by using modified MWCNTs with 8-hydroxyquinoline. When MWCNTs were used to remove metal ions, only 0.3%  $\text{Cd}^{2+}$  ions were removed while modified MWCNTs had a high affinity for the removal of  $\text{Cd}^{2+}$  ions (5.77%) from real water samples (Kosa *et al.* 2012). If we look at the mechanism of ion removal, cadmium ions are removed from the water by ion-exchange as well as adsorption mechanisms. In the ion-exchange mechanism, cadmium ions are exchanged with the protons present on the oxygen atoms of the sidewall functional groups of carbon nanotubes (Figure 1). However, adsorption of cadmium ions on the surface of CNTs is due to strong chemical interaction between the cadmium ions and the surface sites of carbon nanotubes and is known as inner-sphere adsorption, while weaker interaction between cadmium ions and the surface sites of CNTs is known as outer-sphere adsorption.

## Graphene

Graphene possesses a two-dimensional structure of one- or multi-atomic-layered graphites. Graphene is used as another carbon-based nanosorbent, which has good thermal and mechanical properties. A few-layered graphene oxide nanosheets (GOx) were prepared by modified Hummers

method which introduces  $-\text{COOH}$ ,  $-\text{C}=\text{O}$  and  $-\text{OH}$  groups on the surface to increase the sorption capacity of heavy metal ions. Cadmium sorption on graphene oxide nanosheets was carried out in the presence of  $\text{NaClO}_4$  in polyethylene test tubes (Zhao *et al.* 2011b). The sorption of  $\text{Cd}^{2+}$  increased with increasing pH from 6 to 9 because of deprotonation at high pH which made the surface more negative to combine with metal ions. The maximum sorption capacity of  $\text{Cd}^{2+}$  was 106.3 mg/g at pH 6.0 (303 °K). However, the sorption of  $\text{Cd}^{2+}$  on graphene oxide nanosheets decreased with increasing pH in the presence of humic acid because of formation of soluble metal-humic acid complex.

Modified or functionalized graphene was also used for removal of  $\text{Cd}^{2+}$  ions from water samples. Magnetic graphene oxide nanocomposite was synthesized for simultaneous removal of  $\text{Cd}^{2+}$  ions and ionic dyes such as methylene blue and orange G (Deng *et al.* 2013). The maximum sorption capacities in ultrapure water for  $\text{Cd}^{2+}$  ion was 91.29 mg/g. The sorption capacity of nanocomposite was suppressed for  $\text{Cd}^{2+}$  in the presence of methylene blue dye. The sorption capacity for  $\text{Cd}^{2+}$  ion in tap water samples was 65.39% of that in ultrapure water. Functionalized graphene was also fabricated by electrolysis method with potassium hexa-fluorophosphate solution as electrolyte under the static potential of 15 V (Deng *et al.* 2010). Langmuir maximum adsorption capacity observed was



**Figure 1** | Schematic diagram of functionalization of carbon nanotubes sidewall and ion exchange with sidewall groups by cadmium ions in solution.

73.42 mg/g at pH 6.2 and the adsorption equilibrium was achieved in just 40 minutes for cadmium ions. Iron-iron oxide dispersed graphene was used for removal of  $\text{Cd}^{2+}$  ions from water samples (Bhunja *et al.* 2012). Iron oxide nanoparticles in the presence of  $\text{H}_2/\text{Ar}$  atmosphere were transformed to a matrix of iron-iron oxide on the graphene surface at an elevated temperature. Iron-iron oxide dispersed graphene was highly porous and robust. Iron-iron oxide matrix dispersed on reduced graphene oxide (rGO), rGO-Fe(0)- $\text{Fe}_3\text{O}_4$ , with high surface area and high efficiency was basically used for removal of arsenic metal from water samples but it was also used to evaluate adsorption efficiency of other toxic heavy metals like  $\text{Cd}^{2+}$  and  $\text{Hg}^{2+}$  from water. The maximum adsorption capacity of this sorbent was slightly poor towards  $\text{Cd}^{2+}$  ions because the standard reduction potential of  $\text{Cd}^{2+}$  ( $-0.35\text{ V}$ ) was more negative than the other metal ions.

### Carbon-based nanocomposites

It is possible to assemble the nanoscale units in nanocomposites in order to explore their properties. In carbon nanocomposites active materials can be dispersed into a carbon matrix or nanocarbon can be dispersed into a polymer. Various magnetic nanocomposites with carbon-coated nickel structure have been used for removal of heavy metals from water (Xiao *et al.* 2012). Sankaramakrishnan *et al.* (2014) synthesized nanofloral clusters (NFCs) of CNTs over iron and nickel doped activated alumina by CVD for removal of cadmium ion from water. Langmuir maximum adsorption of  $\text{Cd}^{2+}$  ion on nanofloral clusters of CNT (NFC-CNT) was 229.9 mg/g at pH 7.5. A solid-phase extraction method for separation and pre-concentration determination of  $\text{Cd}^{2+}$  ion in environmental samples has been developed by using multi-walled carbon nanotubes/poly(2-amino-thiophenol) nanocomposites (MWCNT-NC) (Nabid *et al.* 2012). The sorbent showed high adsorption affinity for heavy metal ions on macromolecular chains due to the presence of numerous good extractive sites (S and N) of conducting polymer. The maximum adsorption capacity of sorbents at optimum conditions for cadmium ions was found to be 178.7 mg/g at pH 6.0 with the detection limit of 0.3 ng/mL. Recently, nanocarbon conjugated polymer nanocomposites (NCPCs) were

prepared for effective removal of heavy metal ions from water (Khaydarov *et al.* 2010). NCPCs were synthesized from nanocarbon colloids and polyethylenimine. The bonding capacity of NCPC was 5.7 mmol/g at pH 6.0 for most of the divalent metal ions. The sorption percentage of  $\text{Cd}^{2+}$  and other divalent metal ions was higher than 99%. A novel composite of silver with multi-walled carbon nanotubes (Ag-MWCNTs) has been synthesized from functionalized multi-walled carbon nanotubes reduced with N,N-dimethylformamide and cross-linked with silver nitrate for effective removal of  $\text{Cd}^{2+}$  ion (Ramana *et al.* 2013). The Langmuir isotherm model was consistent with the experimental data at different temperatures. Maximum adsorption of  $\text{Cd}^{2+}$  ion was observed at pH 7.0 (more than 90% removal, 10 mg/L initial concentration of cadmium). The thermodynamic parameters indicated that the adsorption process of  $\text{Cd}^{2+}$  ion onto Ag-MWCNTs was endothermic, spontaneous and feasible in the temperature range 293–313 °K.

### RESULT ANALYSES

The reported concentration of cadmium in different environmental water samples is more than the recommended permissible concentration as per WHO guidelines (0.003 mg/L). The reported concentration of cadmium in different environmental water samples are in the range of 0.002–1.46 mg/L (Igwilu *et al.* 2006; Akoteyon 2012; Ambedkar & Muniyan 2012). High concentration of cadmium in water causes different poisonous effects on human beings. Therefore, traditional and nanomaterials are used for removal of cadmium ions from water. Carbon-based nanosorbents are preferred over conventional carbonaceous sorbents because of their high surface area to volume ratio, controlled pore size distribution and they are easy to fabricate on the surface to enhance surface chemistry. Adsorption on the surface of carbon-based nanosorbents is driven by hydrophobic dispersion and weak dipolar forces. This section describes the ranking of carbon-based nanosorbents for removal of cadmium ions on the basis of different parameters and detailed study of adsorption isotherms and kinetics of adsorption of the cadmium ions on carbon-based nanosorbents.

## Ranking of carbon-based nanosorbents for removal of cadmium

The removal efficiency of different synthetic, naturally occurring and waste materials used as adsorbents was 10–80% with respect to the initial cadmium ion concentration. However, adsorption capacity of these materials can be significantly increased by chemical modification on the surface or by pretreatment methods (Rao *et al.* 2010). Various adsorption parameters are required to evaluate their effects on removal efficiency and ranking of carbon-based nanosorbents for removal of cadmium ions from water samples. The adsorption capacity of different carbon-based nanosorbents has been compared at pH 5.0–7.5 and temperature range of 25–30 °C for their selection for treating real water samples. Available important data up to the present is listed in Table 1. Solution pH plays a key role for removal of cadmium from water and wastewater. As can be seen from the reviewed analysis, the removal efficiency of Cd<sup>2+</sup> for all reviewed carbon-based materials tended to increase with increasing pH value. Increasing pH value could precipitate metal as metal hydroxide and the functional groups on the sorbent surface exist in the deprotonated form. However, at low pH, higher concentration and mobility of hydrogen ions favoured hydrogen ions' adsorption rather than metal ions on adsorbent surfaces. The percentage adsorption of Cd<sup>2+</sup> ions increased up to 100% by modified multi-walled carbon nanotubes with 8-hydroxyquinoline when pH increases from 6.0 to 9.0. However, the adsorption capacity of carbon-encapsulated magnetic nanoparticles (CEMNPs) was also better as compared to other reviewed carbon-based nanosorbents at higher pH value. Also, the removal efficiency of Cd<sup>2+</sup> increased up to a limit range with increasing the temperature and time, respectively.


The adsorption capacity of the reviewed carbon-based nanosorbents at pH 5.0–7.5 follows roughly the following order: modified or dispersed MWCNTs > graphene oxide > SWCNTs-COOH > SWCNTs > oxidized CNT > MWCNTs > CNTs (Figure 2). However, the adsorption capacity of carbon-based nanosorbents precisely depends on the type of nanosorbents, e.g., non-functionalized and functionalized nanosorbents. The adsorption capacity of non-functionalized carbon nanotubes (CNTs) follows the following

order: oxidized-CNT > CNTs-Al<sub>2</sub>O<sub>3</sub> > CNTs. Oxidized raw CNTs gave better results in comparison to raw CNTs because of more active oxygen containing groups on the surface of CNTs. The adsorption capacity of functionalized or dispersed multi-walled CNTs follows the following order: NFC-CNT > MWCNTs-NC > MWCNTs-PEG > MWCNTs-MnO<sub>2</sub> > MWCNTs-En > MWCNTs. Modification or dispersion of CNTs can considerably increase the surface area as well as more active sites on the surface. The results analysis also showed that SWCNT-COOH surfaces were more effective toward Cd<sup>2+</sup> ion adsorption than SWCNTs surface because of the carboxyl group which increases negative charge on carbon nanotubes surface. However, SWCNTs offered better performance regarding Cd<sup>2+</sup> ion adsorption than the MWCNTs because of the presence of more active sites on the surface of SWCNTs. It is very difficult to correlate all the reviewed results in terms of all parameters because of their different preparation conditions, purification methods, various size and surface areas of reported sorbents.

The choice of nanosorbents for removal of cadmium also depends on toxicity and reusability of the carbon-based nanosorbents. Although a number of *in vitro* and *in vivo* toxicological studies have been performed, toxicity of carbon nanotubes has not been significantly evaluated because of the number of factors involved. Toxicity of carbon nanotubes depends on many factors, such as their physical form, diameter, length and the nature of attached molecules on the sidewall or surfaces (Wang *et al.* 2009; Firme & Bandaru 2010; Kolosnjaj *et al.* 2010). Also, the results of toxicity are often conflicted at the cellular and whole body levels. The size and length control of CNTs is very important to control the toxicity. Chronic toxicity of CNTs can be reduced by using short CNTs and keeping their length to less than 5 μm (Chawla & Kumar 2013). The functionalization on the surface of carbon nanotubes improves their biocompatibility and reduces the toxic effects (Chawla & Kumar 2014). It was found that at a particular concentration, surface modification or functionalization reduce the toxicity of carbon nanotubes (Foldvari & Bagonluri 2008). Thus, it can be concluded that modified or functionalized carbon nanotubes with smaller size and smaller length may be the best sorbent for removal of cadmium metal ions in terms of toxicity. In addition, further studies are required in this area to make these materials safer and

**Table 1** | Carbon-based nanosorbents for removal of cadmium metal ions from aqueous solution

Carbon-based adsorbent	Preparation method	Max. ads. capacity of Cd <sup>2+</sup> (mg/g)	Other target metal ions M(II)	Temp. (K)	pH	Surface area (m <sup>2</sup> /g)/Particle size (nm)	Reg. coeff. (R <sup>2</sup> )	Isotherms/ Kinetics	Reference
Carbon nanotubes (CNTs)	Commercially available	1.1	–	298	5.5	122/–	–	–	Li <i>et al.</i> (2003b)
(CEMNPs)	Carbon arc plasma	91.0	–	Room temp. (RT)	8.0	–/40–90	0.998	Langmuir/ Pseudo-second-order	Pyrzynska (2010)
CNTs on micro-sized Al <sub>2</sub> O <sub>3</sub>	Electroless plating in CH <sub>4</sub> atmosphere at 700 °C	8.89	Pb, Cu	RT	6.6	18.61/30–80	0.956	Langmuir/ Pseudo-second-order	Hsieh & Horng (2007)
KMnO <sub>4</sub> oxidized CNTs	Oxidation method	11.0	–	298	5.5	128/10–30	–	–	Li <i>et al.</i> (2003b)
SWCNT	Chemical vapour deposition	24.07	Pb, Cu	293	5.0	400/1–2	0.999	Langmuir/–	Moradi <i>et al.</i> (2011)
SWCNT-COOH	Purchased from NanoAmor Nanostructured & Amorphous Materials, Inc., USA	55.89	Pb, Cu	293	5.0	400/1–2	0.999	Langmuir/–	Moradi <i>et al.</i> (2011)
MWCNTs	Commercially available	10.86	Pb, Cu	RT	5.0	–	0.998	–	Li <i>et al.</i> (2003a)
MWCNT-PEG	MWCNTs + oxidation by SOCl <sub>2</sub> + amination by PEG-NH <sub>2</sub>	77.60	Pb, As(V)	298	4.0	22.4/17.4	0.999	Koble–Corrigan/ Weber–Morris	Velickovic <i>et al.</i> (2013)
MWCNT-En	Chemical modification	25.7	–	298	8.0	–	0.999	Langmuir/ Pseudo-second-order	Vukovic <i>et al.</i> (2010)
MWCNT-NC	Chemical method	178.70	Pb	RT	6.0	–	–	–	Nabid <i>et al.</i> (2012)
MWCNT-MnO <sub>2</sub>	Chemical method	41.6	–	298	6.0	–	0.999	Langmuir/ Pseudo-second-order	Luo <i>et al.</i> (2013)
Layered Gox	Hummers method	106.3	Co	303	6.0	–	0.999	Langmuir/–	Zhao <i>et al.</i> (2011a)
NFC-CNT	Chemical vapour deposition	229.9	Cr(VI)	–	7.5	–	0.999	Langmuir/–	Sankararamakrishnan <i>et al.</i> (2014)



**Figure 2** | Adsorption of cadmium by different carbon-based nanomaterials from water samples at pH 4.0–7.5 and temperature range 25–30 °C.

compatible for different applications. Regeneration is another very important aspect for ranking of these nanomaterials. Carbon nanotubes can be regenerated and reused for removal of heavy metal ions. Regeneration significantly reduces the overall costs of the procedure. Regeneration and recycling of carbon nanotubes were evaluated in detail for a number of heavy metal ions (Wang *et al.* 2007; Tehrani *et al.* 2013). There are very few studies available to date for regeneration of carbon nanotubes for cadmium metal ions (Hsieh & Horng 2007; Kosa *et al.* 2012). Most of the metal ions desorbed on the surface of carbon nanotubes in acidic medium (pH lower than 2.0) and could be used without losing efficiency for up to three cycles. Research adopting standard and similar procedures while considering all parameters in all aspects is further required for finding the most efficient, cheapest and safest alternatives for removal of cadmium ions from water.

### Adsorption isotherms of carbon-based nanosorbents

Langmuir and Freundlich adsorption isotherms are quite helpful in determining the adsorption capacity of an adsorbent (Li *et al.* 2004; Hsieh & Horng 2007). In the reviewed nanosorbents, the Langmuir isotherm gave the better value of regression coefficient ( $R^2 \sim 0.999$ ) compared to Freundlich isotherm ( $R^2 \sim 0.979$ ) which indicates monolayer coverage of the cadmium ions on the surface of the adsorbent (Lv *et al.* 2005; Moradi *et al.* 2010; Pyrzyńska 2010; Kabbashi *et al.* 2011; Moradi & Zare 2011; Zhao *et al.* 2011a, b). It is based on the assumption that maximum adsorption occurs when a saturated monolayer of metal ions is present on the adsorbent surface. The Langmuir equation

(Langmuir 1918) for monolayer coverage of the metal ions on the surface of the adsorbent is expressed as follows:

$$q_e = (q_m K_L C_e) / (1 + K_L C_e) \quad (1)$$

A linear form of the Langmuir equation can be expressed as:

$$C_e/q_e = 1/(q_m K_L) + C_e/q_m \quad (2)$$

where  $q_e$  is the equilibrium amount adsorbed (mg/g),  $q_m$  is maximum adsorbed metal ion amount to complete monolayer coverage (mg/g),  $K_L$  is Langmuir constant related to energy of adsorption,  $C_e$  is equilibrium concentration of metal ions (mg/L). The value of  $K_L$  is used to calculate essential characteristics of Langmuir isotherms called dimensionless separation parameter  $R_L$  (Hall *et al.* 1966; Annadurai & Krishnan 1997):

$$R_L = 1/(1 + K_L C_0) \quad (3)$$

where  $K_L$  is Langmuir constant and  $C_0$  is initial concentration of metal ions in (mg/L). The value of separation factor indicates shape or type of isotherms. Isotherm will be linear if  $R_L = 1$ , irreversible if  $R_L = 0$ , favourable if  $0 < R_L < 1$  and unfavourable if  $R_L > 1$ . The value of separation factor and regression coefficient calculated by the Langmuir isotherms model for most of the carbon-based nanomaterials is less than 1 ( $R_L < 1$  and  $R^2 \sim 0.999$ ) which indicates favourable and mono-layered coverage of the cadmium ions on the surface of the carbon-based nanosorbents (Li *et al.* 2004; Lv *et al.* 2005; Hsieh & Horng 2007; Moradi *et al.* 2010; Pyrzyńska 2010; Vukovic *et al.* 2010; Kabbashi *et al.* 2011; Moradi & Zare 2011; Luo *et al.* 2013).

The Freundlich isotherm is basically an empirical relationship used to describe the adsorption on heterogeneous adsorbent surface (Freundlich 1906). The Freundlich equation can be expressed as follows:

$$q_e = K_F C_e^{1/n} \quad (4)$$

where  $q_e$  is the equilibrium amount adsorbed (mg/g),  $K_F$  and  $n$  are Freundlich constants corresponding to adsorption

capacity and adsorption intensity respectively. A linear form of the Freundlich equation can be expressed as:

$$\log q_e = \log K_F + 1/n \log C_e. \quad (5)$$

The value of  $n$  varies in the range of 1–10 for classification of favourable adsorption (Chantawong *et al.* 2003). The high value of  $1/n$  indicates preferential and high adsorption intensity toward adsorbent (Li *et al.* 2004). However, the high value of Freundlich constants  $K_F$  indicates greater adsorption tendency toward adsorbent. In some cases the adsorption process of cadmium ions on adsorbent surfaces has been described by the Koble–Corrigan adsorption isotherm which is a three-parameter equation incorporating Langmuir and Freundlich adsorption isotherms (Velickovic *et al.* 2013). The Koble–Corrigan adsorption isotherm is also used for heterogeneous adsorbent surface (Koble & Corrigan 1952). The values of regression coefficients ( $R^2$ ) calculated by the Langmuir model were higher for most of the carbon-based nanosorbents compared to the Freundlich model. Therefore, adsorption of cadmium ions on most of the carbon-based nanosorbents is defined by Langmuir isotherms implying the monolayer coverage of the cadmium ions on the surface of the carbon-based nanosorbents.

### Kinetic study of carbon-based nanosorbents

Adsorption of metal ions on the adsorbent surfaces can be easily explained by different kinetic models, e.g., pseudo-first-order (Lagergren 1898), pseudo-second-order (Demirbas *et al.* 2002) and diffusion or intra-particle diffusion kinetic models (Weber & Morris 1963). Kinetic models are also helpful to describe the mechanism of adsorption of metal ions on the adsorbent surface. The pseudo-first-order kinetic model was given by Lagergren in 1898 for solid–liquid system and can be expressed by:

$$dq_t/dt = k_1(q_e - q_t) \quad (6)$$

A linear form of the equation is:

$$\ln(q_e - q_t) = \ln(q_e) - k_1 t \quad (7)$$

where  $k_1$  is the adsorption rate constant of first-order kinetic models in L/mg/min,  $q_e$  is equilibrium amount adsorbed at

time  $t$  (mg/g) and  $q_t$  is equilibrium amount adsorbed at time  $t = \infty$ . The values of  $k_1$  were calculated from the slope of the linear plot of  $\ln(q_e - q_t)$  versus  $t$ .

The pseudo-second-order kinetic models can be expressed by (Demirbas *et al.* 2004):

$$dq_t/dt = k_2(q_e - q_t)^2 \quad (8)$$

A linear form of the equation is:

$$t/q_t = 1/k_2 q_e^2 + t/q_e \quad (9)$$

where  $k_2$  is the adsorption rate constant of second-order kinetic models in L/mg/min,  $q_e$  is equilibrium amount adsorbed at time  $t$  (mg/g) and  $q_t$  is equilibrium amount adsorbed at time  $t = \infty$ . The values of  $q_e$  and  $k_2$  can be calculated by the slope and intercept plot of  $t/q_t$  versus  $t$ .

The results showed that the experimental  $q_e$  values for cadmium ions observed by using carbon nanoparticles (Pyrzynska 2010), carbon nanotubes (Hsieh & Horng 2007; Moradi *et al.* 2010; Moradi & Zare 2011) and modified multi-walled carbon nanotubes (Vukovic *et al.* 2010; Luo *et al.* 2013) have good agreement with the calculated value of saturation amount with the pseudo-second-order kinetic models. Conformity between the predicted value calculated by kinetic model and experimental value was expressed by correlation coefficient ( $R^2$ ). The value of correlation coefficient ( $R^2$ ) was close to 1 and the relatively high value of correlation coefficient is the more applicable model to represent the adsorption mechanism. The value of correlation coefficients ( $R^2$ ) of the pseudo-first-order model were slightly less than the pseudo-second-order model for most of the carbon-based nanosorbents which indicates that the kinetic model is best explained by the pseudo-second-order model rather than the pseudo-first-order model. This indicates that adsorption of cadmium onto carbon-based nanosorbents may be explained by chemisorption mechanism which involves the valence forces through exchange or sharing of electrons between nanosorbents and cadmium ions.

In addition, initially at higher concentration the rate controlling step may be either the pore diffusion, boundary diffusion or the intra-particle diffusion of the cadmium

ions on the surface of carbon-based nanosorbents (Velickovic *et al.* 2013). The slowest of the three steps controls the overall rate of the method. The equilibrium amount adsorbed on carbon-based nanosorbents is now a function of half time ( $t^{1/2}$ ) rather than time ( $t$ ) to show the diffusion mechanism suggested by Weber and Morris as follows:

$$q_t = k_{ip}t^{1/2} + C \quad (10)$$

where  $k_{ip}$  is the intra-particle diffusion rate constant ( $\text{mg/g min}^{1/2}$ ) and  $C$  ( $\text{mg/g}$ ) is a constant representing the film thickness.

For all reviewed carbon-based nanosorbents, the kinetic data were fitted to pseudo-first-order and intra-particle diffusion models for an initial period of the first reaction step only. However, there was better correlation to the pseudo-second-order model over a long period of time for most of the systems studied (Hsieh & Horng 2007; Moradi *et al.* 2010; Pyrzyńska 2010; Vukovic *et al.* 2010; Moradi & Zare 2011; Luo *et al.* 2013).

## CONCLUSION

The remarkable physical and chemical properties of carbon-based nanomaterials make these materials excellent candidates for waste water treatment. The aim of this review is to compare the maximum sorption capacity for  $\text{Cd}^{2+}$  ions by carbon-based nanomaterials from aqueous solutions. However, the comparison of maximum sorption capacity for  $\text{Cd}^{2+}$  is restricted by several parameters, such as characteristics of sorbents prepared in a similar way with similar properties, i.e., surface area, surface total active sites, surface acidity, point of zero charge and also the solution properties such as pH of solution, time of contact of solution, initial metal ions concentration, etc. In conclusion, adsorption capacity of the reviewed carbon-based nanosorbents at pH 5.0–7.5 follows the following order: modified or dispersed MWCNTs > graphene oxide > SWCNT-COOH > SWCNTs > oxidised-CNT > MWCNTs > CNTs. The removal capacity of functionalized carbon nanotubes was found to be higher than the non-functionalized carbon nanotubes. Nanofloral clusters of carbon nanotubes over alumina (NFC-CNT) were found to be the best carbon-based nanomaterial for

removal of cadmium ions from water at pH 7.5. Modification or dispersion of CNTs can considerably improve the adsorption capacity by providing more active binding sites. The amount of the contaminant cadmium that binds to the modified or dispersed MWCNTs is much higher than the AC due to  $\pi$ - $\pi$  electron-donor acceptor properties of the modified or dispersed MWCNTs. Removal of cadmium from water takes place mainly by monolayer coverage on the adsorbent surface adopted Langmuir isotherm with great value of regression coefficient. The identified knowledge gaps are unavailability of systematic studies including similar preparation method, purity, size and surface areas of carbon-based nanomaterials. Most of the research is still based on laboratory scale only, therefore how to utilize all these nanomaterials for industrial application is still a challenging interest. It is also necessary to study the potential health risks and environmental impacts of carbon-based nanomaterials before their widespread use in different applied fields.

## ACKNOWLEDGEMENTS

The authors are grateful to the administration and management of Manav Rachna International University Faridabad, India, for providing infrastructure and other support for preparation of this review and other ongoing research.

## REFERENCES

- Akesson, A. 2011 Cadmium exposure in the environment: Renal effects and the benchmark dose. *Encycl. Environ. Health* 49 (4), 465–473.
- Akoteyon, I. S. 2012 Evaluation of ground water quality using contamination index in parts of Alimosho, Lagos-Nigeria. *Am. Acad. Scho. Res. J.* 4 (4), 1–6.
- Ambedkar, G. & Muniyan, M. 2012 Analysis of heavy metals in water, sediments and selected freshwater fish collected from Gadilam river, Tamilnadu, India. *Int. J. Toxicol. Appl. Pharmacol.* 2 (2), 25–30.
- Amin, N., Hussain, A., Alamzeb, S. & Begum, S. 2013 Accumulation of heavy metals in edible parts of vegetables irrigated with waste water and their daily intake to adults and

- children, District Mardan, Pakistan. *Food Chem.* **136** (3–4), 1515–1523.
- Ando, Y., Zhao, X., Sugai, T. & Kumar, M. 2004 Growing carbon nanotubes. *Mat. Today* **7** (10), 22–29.
- Annadurai, G. & Krishnan, M. R. V. 1997 Batch equilibrium adsorption of reactive dye on to natural biopolymer. *Iranian Poly. J.* **6** (3), 169–172.
- Balasubramanian, K. & Burghard, M. 2005 Chemically functionalized carbon nanotubes. *Small* **1** (2), 180–192.
- Bhunia, P., Kim, G., Baik, C. & Lee, H. 2012 A strategically designed porous iron–iron oxide matrix on graphene for heavy metal adsorption. *Chem. Commun.* **48**, 9888–9890.
- Bolan, N. S., Makino, T., Kunhikrishnan, A., Kim, P., Ishikawa, S., Murakami, M., Naidu, R. & Kirkham, M. B. 2013 Chapter four-cadmium contamination and its risk management in rice ecosystems. *Adv. Agronomy* **119**, 183–273.
- Chantawong, V., Harvey, N. W. & Bashkin, V. N. 2003 Comparison of heavy metal adsorptions by Thaikaolin and ball clay. *Water Air Soil Pollut.* **148**, 111–125.
- Charentanyarak, L. 1999 Heavy metals removal by chemical coagulation and precipitation. *Water Sci. Technol.* **39** (10–11), 135–138.
- Chawla, J. & Kumar, A. 2013 Ranking carbon-based nanomaterials using cytotoxicity to minimize public health risks. *Int. J. Environ. Eng. Manage.* **4** (4), 301–308.
- Chawla, J. & Kumar, A. 2014 Reducing the toxicity of carbon nanotubes and fullerenes using surface modification strategy. (N. Janardhana Raju, Wolfgang Gossel, A. L. Ramanathan and M. Sudhakar, eds). *Management of Natural Resources in the Changing Environment*. Capital Publishing, New Delhi, pp. 176–188.
- Ciarrocca, M., Capozzella, A., Tomei, F., Tomei, G. & Caciari, T. 2013 Exposure to cadmium in male urban and rural workers and effects on FSH, LH and testosterone. *Chemosphere* **90** (7), 2077–2084.
- Cimino, G., Passerini, A. & Toscano, G. 2000 Removal of toxic cations and Cr(VI) from aqueous solution by hazelnut shell. *Water Res.* **34** (11), 2955–2962.
- Dabrowski, A., Hubicki, Z., Podkoscielny, P. & Robens, E. 2004 Selective removal of the heavy metal ions from waters and industrial wastewaters by ion-exchange method. *Chemosphere* **56** (2), 91–106.
- Demirbas, E., Kobya, M., Oncel, S. & Sencan, S. 2002 Removal of Ni(II) from aqueous solution by adsorption onto hazelnut shell activated carbon: equilibrium studies. *Bioresour. Technol.* **84** (1), 291–295.
- Demirbas, E., Kobya, M., Senturk, E. & Ozkan, T. 2004 Adsorption kinetics for the removal of chromium(VI) from aqueous solutions on the activated carbons prepared from agricultural wastes. *Water S.A.* **30** (4), 533–539.
- Deng, J. H., Zhang, X. R., Zeng, G. M., Gong, J. L., Niu, Q. Y. & Liang, J. 2013 Simultaneous removal of Cd(II) and ionic dyes from aqueous solution using magnetic graphene oxide nanocomposite as an adsorbent. *Chem. Eng. J.* **226** (1), 189–200.
- Deng, X., Lu, L., Li, H. & Luo, F. 2010 The adsorption properties of Pb(II) and Cd(II) on functionalized graphene prepared by electrolysis method. *J. Hazard. Mater.* **183** (1–3), 923–930.
- EPA 2008 *The Provision and Quality of Drinking Water in Ireland: A Report for the Year*. Environmental Protection Agency, 102 pp.
- Feng, J., Sui, J., Cai, W. & Gao, Z. 2008 Microstructure and mechanical properties of carboxylated carbon nanotubes/poly(L-lactic acid) composite. *J. Compos. Mater.* **42**, 1587–1595.
- Firme, C. P. & Bandaru, P. R. 2010 Toxicity issues in the application of carbon nanotubes to biological systems. *Nanomedicine* **6** (2), 245–256.
- Foldvari, M. & Bagonluri, M. 2008 Carbon nanotubes as functional excipients for nanomedicines: II. Drug delivery and biocompatibility issues. *Nanomedicine* **4**, 183–200.
- Fowler, B. A. 2009 Monitoring of human populations for early markers of cadmium toxicity: A review. *Toxicol. Appl. Pharmacol.* **238** (3), 294–300.
- Freundlich, H. M. F. 1906 Over the adsorption in solution. *J. Phys. Chem.* **57**, 385–470.
- Fu, F. & Wang, Q. 2011 Removal of heavy metal ions from wastewaters: A review. *J. Environ. Manage.* **92** (3), 407–418.
- Gao, Z., Badosz, T. J., Zhao, Z., Han, M. & Qiu, J. 2009 Investigation of factors affecting adsorption of transition metals on oxidized carbon nanotubes. *J. Hazard. Mater.* **167** (1–3), 357–365.
- Gauden, P. A., Terzyk, A. P., Rychlicki, G., Kowalczyk, P., Lota, K., Raymundo-Pinero, E., Frackowiak, E. & Beguin, F. 2006 Thermodynamic properties of benzene adsorbed in activated carbons and multi-walled carbon nanotubes. *Chem. Phys. Lett.* **421** (4–6) 409–414.
- Ghodbane, I., Nouri, L., Hamdaoui, O. & Chiha, M. 2007 Kinetic and equilibrium study for the adsorption of cadmium(II) ions from aqueous phase by eucalyptus bark. *J. Hazard. Mater.* **152** (1), 148–158.
- Ghorbani, M. & Eisazadeh, H. 2013 Removal of COD, color, anions and heavy metals from cotton textile wastewater by using polyaniline and polypyrrole nanocomposites coated on rice husk ash. *Composites B: Eng.* **45** (1), 1–7.
- Hall, K. R., Eagleton, L. C., Axerivos, A. & Vermeuleu, T. 1966 Pore and solid diffusion kinetics in fixed bed adsorption under constant pattern conditions. *Ind. Eng. Chem. Fun Fam.* **5** (2), 212–216.
- Han, N. & Ho, J. C. 2014 *3-One-Dimensional Nanomaterials for Energy Applications*. Nanocrystalline Materials, 2nd edn, Elsevier, Oxford, pp. 75–120.
- Horiguchi, H., Oguma, E., Sasaki, S., Miyamoto, K., Ikeda, Y., Machida, M. & Kayama, F. 2004 Comprehensive study of the effects of age, iron deficiency, diabetes mellitus, and cadmium burden on dietary cadmium absorption in cadmium-exposed female Japanese farmers. *Toxicol. Appl. Pharmacol.* **196** (1), 114–123.
- Hsieh, S. H. & Horng, J. J. 2007 Adsorption behavior of heavy metal ions by carbon nanotubes grown on microsized Al<sub>2</sub>O<sub>3</sub>

- particles. *J. Univ. Sci. Tech. Beijing, Min. Metall. Mat.* **14** (1), 77–84.
- Hu, J., Chen, G. H. & Lo, I. M. C. 2006 Selective removal of heavy metals from industrial wastewater using maghemite nanoparticle: Performance and mechanisms. *J. Environ. Eng.* **132** (7), 709–715.
- Hua, M., Zhang, S., Pan, B., Zhang, W., Lv, L. & Zhang, Q. 2012 Heavy metal removal from water/wastewater by nanosized metal oxides: A review. *J. Hazard. Mater.* **211–212** (1), 317–331.
- Hutton, M. & Symon, C. 1986 The quantities of cadmium, lead, mercury and arsenic entering the U.K. environment from human activities. *Sci. Total Environ.* **57**, 129–150.
- Igwilo, I. O., Afonne, O. J., Maduabuchi, U. J. & Orisakwe, O. E. 2006 Toxicological study of the Anam river in Otuocha, Anambra state, Nigeria. *Archi. Environ. Occupat. Health* **61** (5), 205–208.
- Iijima, S. 1991 Helical microtubules of graphitic carbon. *Nature* **354**, 56–58.
- Iijima, S. & Ichihashi, T. 1993 Single-shell carbon nanotubes of 1-nm diameter. *Nature* **363**, 603–605.
- Jarup, L. & Akesson, A. 2009 Current status of cadmium as an environmental health problem. *Toxicol Appl. Pharmacol.* **238** (3), 201–208.
- John, S. & Santhi, S. 1994 Electroplated cobalt-cadmium selective solar absorbers. *Solar Energy Mat. Solar Cells* **33** (4), 505–516.
- Kabbashi, N. A., Daoud, J. I., Isam, Y. Q., Mirghami, M. E. S. & Rosli, N. F. 2011 Statistical analysis for removal of cadmium from aqueous solution at high pH. *Aust. J. Bas. App. Sci.* **5** (6), 440–446.
- Kadirvelu, K. & Namasivayam, C. 2003 Activated carbon from coconut coirpith as metal adsorbent: adsorption of  $Cd^{2+}$  from aqueous solution. *Adv. Environ. Res.* **7** (2), 471–478.
- Khan, S., Cao, Q., Zheng, Y. M., Huang, Y. Z. & Zhu, Y. G. 2008 Health risks of heavy metals in contaminated soils and food crops irrigated with wastewater in Beijing, China. *Environ. Pollut.* **152** (3), 686–692.
- Khani, H. & Moradi, O. 2013 Influence of surface oxidation on the morphological and crystallographic structure of multi-walled carbon nanotubes via different oxidants. *J. Nanostruct. Chem.* **3**, 73–80.
- Khaydarov, R. A., Khaydarov, R. R. & Gapurova, O. 2010 Water purification from metal ions using carbon nanoparticle-conjugated polymer nanocomposites. *Water Res.* **44** (6), 1927–1933.
- Koble, R. A. & Corrigan, T. E. 1952 Adsorption isotherms for pure hydrocarbons. *Ind. Eng. Chem.* **44**, 383–387.
- Kolosnjaj, T. J., Hartman, K. B. & Boudjemaa, S. 2010 In vivo behavior of large doses of ultrashort and full-length single-walled carbon nanotubes after oral and intraperitoneal administration to Swiss mice. *Am. Chem. Soc. Nano.* **4** (3), 1481–1492.
- Kosa, S. A., Zhrania, G. A. & Salam, M. A. 2012 Removal of heavy metals from aqueous solutions by multi-walled carbon nanotubes modified with 8-hydroxyquinoline. *Chem. Eng. J.* **181–182**, 159–168.
- Krishna, K. S., Li, Y., Li, S. & Kumar, C. S. S. R. 2013 Lab-on-a-chip synthesis of inorganic nanomaterials and quantum dots for biomedical applications. *Adv. Drug Del. Rev.* **65**(11–12), 1470–1495.
- Kumar, R. & Chawla, J. 2014 Removal of cadmium ion from water/wastewater by nano-metal oxides: A review. *Water Qual. Exp. Health* **5** (4), 215–226.
- Lagergren, S. 1898 About the theory of so-called adsorption of soluble substances. *K. Sven. Vetenskapsakad. Handlingar Band* **24** (1), 1–39.
- Lambert, R., Grant, C. & Sauve, S. 2007 Cadmium and zinc in soil solution extracts following the application of phosphate fertilizers. *Sci. Total Environ.* **378** (3), 293–305.
- Langmuir, I. 1918 The adsorption of gases on plane surfaces of glass, mica and platinum. *J. Am. Chem. Soc.* **40** (9), 1361–1403.
- Lee, J. S. & Jang, J. 2014 Hetero-structured semiconductor nanomaterials for photocatalytic applications. *J. Ind. Eng. Chem.* **20** (2), 363–371.
- Li, Q. S., Chen, Y., Fu, H. B., Cui, Z., Shi, L., Wang, L. L. & Liu, Z. F. 2012 Health risk of heavy metals in food crops grown on reclaimed tidal flat soil in the Pearl River Estuary, China. *J. Hazard. Mater.* **227–228**, 148–154.
- Li, X., Tang, Y., Xuan, Z., Liu, Y. & Luo, F. 2007 Study on the preparation of orange peel cellulose adsorbents and biosorption of  $Cd^{2+}$  from aqueous solution. *Sep. Purif. Technol.* **55** (1), 69–75.
- Li, Y. H., Ding, J., Luan, Z., Di, Z., Zhu, Y., Xu, C., Wu, D. & Wei, B. 2003a Competitive adsorption of  $Pb^{2+}$ ,  $Cu^{2+}$  and  $Cd^{2+}$  ions from aqueous solutions by multi-walled carbon nanotubes. *Carbon* **41** (14), 2787–2792.
- Li, Y. H., Wang, S., Luan, Z., Ding, J., Xu, C. & Wu, D. 2003b Adsorption of cadmium(II) from aqueous solution by surface oxidized carbon nanotubes. *Carbon* **41** (5), 1057–1062.
- Li, Y. H., Wang, S., Zhang, X., Wei, J., Xu, C., Luan, Z. & Wu, D. 2003c Adsorption of fluoride from water by aligned carbon nanotubes. *Mater. Res. Bull.* **38** (3) 469–476.
- Li, Y. H., Di, Z., Luan, Z. K., Ding, J., Zuo, H., Wu, X. Q., Xu, C. L. & Wu, D. H. 2004 Removal of heavy metals from aqueous solution by carbon nanotubes: adsorption equilibrium and kinetics. *J. Environ. Sci.* **16** (2), 208–211.
- Lo, S. F., Wang, S. Y., Tsai, M. J. & Lin, L. D. 2012 Adsorption capacity and removal efficiency of heavy metal ions by Moso and Ma bamboo activated carbons. *Chem. Eng. Res. Design* **90** (9), 1397–1406.
- Luo, C., Wei, R., Guo, D., Zhang, S. & Yan, S. 2013 Adsorption behavior of  $MnO_2$  functionalized multi-walled carbon nanotubes for the removal of cadmium from aqueous solutions. *Chem. Eng. J.* **225**, 406–415.
- Lv, L., Hor, M., Su, F. & Zhao, X. 2005 Competitive adsorption of  $Pb^{2+}$ ,  $Cu^{2+}$ , and  $Cd^{2+}$  ions on microporous titanosilicate ETS-10. *J. Colloid Interface Sci.* **287** (1), 178–184.
- Mahalik, M. P., Hitner, H. W. & Prozialeck, W. C. 1995 Teratogenic effects and distribution of cadmium ( $Cd^{2+}$ ) administered via osmotic minipumps to gravid Cf-1 mice. *Toxicol. Lett.* **76** (3), 195–202.

- Martinis, E. M., Olsina, R. A., Altamirano, J. C. & Wuilloud, R. G. 2009 On-line ionic liquid-based preconcentration system coupled to flame atomic absorption spectrometry for trace cadmium determination in plastic food packaging materials. *Talanta* **78** (3), 857–862.
- Memon, S. Q., Memon, N., Shaw, S. W., Khuhawar, M. Y. & Bhangar, M. I. 2007 Saw dust—A green economical sorbent for the removal of cadmium(II) ions. *J. Hazard. Mater.* **139** (1), 116–121.
- Mhiaoui, S., Sar, F. & Gasser, J. G. 2005 Influence of the history of a melt on the electrical resistivity of cadmium–antimony liquid alloys. *Intermetallics* **11** (11–12), 1377–1382.
- Moradi, O. 2011 The removal of ions by functionalized carbon nanotube: equilibrium, isotherms and thermodynamic studies. *Chem. Biochem. Eng. Q.* **25** (2), 229–240.
- Moradi, O. & Zare, K. 2011 Adsorption of Pb(II), Cd(II) and Cu(II) ions from aqueous solution onto SWCNTs and SWCNT–COOH surfaces: Kinetics study. *Fullerenes Nanotubes Carbon Nanostruct.* **19**, 628–652.
- Moradi, O., Aghaie, M., Zare, K., Monajjemi, M. & Aghaie, H. 2009 The study of adsorption characteristics Cu<sup>2+</sup> and Pb<sup>2+</sup> ions onto PHEMA and P(MMA-HEMA) surfaces from aqueous single solution. *J. Hazard. Mater.* **170**, 673–679.
- Moradi, O., Zare, K., Monajjemi, M., Yari, M. & Aghaie, H. 2010 The studies of equilibrium and thermodynamic adsorption of Pb(II), Cd(II) and Cu(II) ions from aqueous solution onto SWCNTs and SWCNT–COOH surfaces. *Fullerenes Nanotubes Carbon Nanostruct.* **18** (3), 285–302.
- Moradi, O., Zare, K. & Yari, M. 2011 Interaction of some heavy metal ions with single walled carbon nanotube. *Int. J. Nano. Dim.* **1** (3), 203–220.
- Moradi, O., Yari, M., Zare, K., Mirza, B. & Najafi, F. 2012 Carbon nanotubes: A review of chemistry principles and reactions. *Fuller. Nanotub. Carbon Nanostruct.* **20** (2), 138–151.
- Nabid, M. R., Sedghi, R., Bagheri, A., Behbahani, M., Taghizadeh, M., Oskooie, H. A. & Heravi, M. M. 2012 Preparation and application of poly(2-amino thiophenol)/MWCNTs nanocomposite for adsorption and separation of cadmium and lead ions via solid phase extraction. *J. Hazard. Mater.* **203–204**, 93–100.
- Najafi, F., Norouzi, M., Zare, K. & Fakhri, A. 2013 Removal of ethidium bromide by carbon nanotube in aqueous solution: isotherms, equilibrium mechanism studies, and its comparison with nanoscale of zero valent iron as adsorbent. *J. Nanostruct. Chem.* **3**, 60–66.
- Ngomsik, A. F., Bee, A., Draye, M., Cote, G. & Cabuil, V. 2005 Magnetic nano- and microparticles for metal removal and environmental applications: a review. *C.R. Chim.* **8** (6), 963–970.
- Ok, Y. S., Usman, A. R. A., Lee, S. S., Abd El-Azeem, S. A. M., Choi, B., Hashimoto, Y. & Yang, J. E. 2011 Effects of rapeseed residue on lead and cadmium availability and uptake by rice plants in heavy metal contaminated paddy soil. *Chemosphere* **85** (4), 677–682.
- Panda, G. C., Das, S. K., Chatterjee, S., Maity, P. B., Bandopadhyay, T. S. & Guha, A. K. 2006 Adsorption of cadmium on husk of *Lathyrus sativus*: Physico-chemical study. *Colloid Surf. B Biointerfaces* **50** (1), 49–54.
- Pyrzynska, K. 2010 Sorption of Cd<sup>2+</sup> onto carbon-based materials, a comparative study. *Microchimica Acta* **169**, 7–13.
- Qdais, H. A. & Moussa, H. 2004 Removal of heavy metals from wastewater by membrane processes: a comparative study. *Desalination* **164** (2), 105–110.
- Ramana, D. K. V., Yu, J. S. & Seshiaiah, K. 2013 Silver nanoparticles deposited multiwalled carbon nanotubes for removal of Cu(II) and Cd(II) from water: Surface, kinetic, equilibrium, and thermal adsorption properties. *Chem. Eng. J.* **223** (1), 806–815.
- Rao, K. S., Mohapatra, M., Anand, S. & Venkateswarlu, P. 2010 Review on cadmium removal from aqueous solutions. *Int. Eng. Sci. Tech.* **2** (7), 81–103.
- Salam, M. A. 2013 Removal of heavy metal ions from aqueous solutions with multi-walled carbon nanotubes: Kinetic and thermodynamic studies. *Int. J. Environ. Sci. Technol.* **10** (4), 677–688.
- Salam, M. A., Makki, M. S. I. & Abdelaal, M. Y. A. 2011 Preparation and characterization of multi-walled carbon nanotubes/chitosan nanocomposite and its application for the removal of heavy metals from aqueous solution. *J. Alloy. Comp.* **509** (5), 2582–2587.
- Salam, M. A., Zhrani, G. A. & Kosa, S. A. 2012 Simultaneous removal of copper(II), lead(II), zinc(II) and cadmium(II) from aqueous solutions by multi-walled carbon nanotubes. *Comp. Rend. Chim.* **15** (5), 398–408.
- Sankaramakrishnan, N., Jaiswal, M. & Verma, N. 2014 Composite nanofloral clusters of carbon nanotubes and activated alumina: An efficient sorbent for heavy metal removal. *Chem. Eng. J.* **235** (1), 1–9.
- Shamsudin, M. S., Mohammad, M., Zobir, S. A. M., Asli, N. A., Bakar, S. A., Abdullah, S., Yahya, S. Y. S. & Mahmood, M. R. 2013 Synthesis and nucleation-growth mechanism of almost catalyst-free carbon nanotubes grown from Fe-filled sphere-like graphene-shell surface. *J. Nanostruct. Chem.* **3**, 13–24.
- Sharma, A. & Bhattacharyya, K. G. 2005 *Azadirachta indica* (Neem) leaf powder as a biosorbent for removal of Cd(II) from aqueous medium. *J. Hazard. Mater.* **125** (1–3), 102–112.
- Sheikh, A. H. E. 2008 Effect of oxidation of activated carbon on its enrichment efficiency of metal ions: comparison with oxidized and non-oxidized multi-walled carbon nanotubes. *Talanta* **75** (1), 127–134.
- Singh, A., Sharma, R. K., Agrawal, M. & Marshall, F. M. 2010 Health risk assessment of heavy metals via dietary intake of foodstuffs from the wastewater irrigated site of a dry tropical area of India. *Food Chem. Toxicol.* **48** (2) 611–619.
- Singh, R. P. & Agrawal, M. 2010 Variations in heavy metal accumulation, growth and yield of rice plants grown at different sewage sludge amendment rates. *Ecotoxicol. Environ. Safety* **73** (4), 632–641.
- Sud, D., Mahajan, G. & Kaur, M. P. 2008 Agricultural waste material as potential adsorbent for sequestering heavy metal

- ions from aqueous solutions – A review. *Bioresource Technol.* **99** (14), 6017–6027.
- Swaddiwudhipong, W., Limpatanachote, P., Mahasakpan, P., Krintratun, S., Punta, B. & Funkhiew, T. 2012 Progress in cadmium-related health effects in persons with high environmental exposure in northwestern Thailand: A five-year follow-up. *Environ. Res.* **112**, 194–198.
- Tadjarodi, A., Imani, M. & Kerdari, H. 2013 Adsorption kinetics, thermodynamic studies, and high performance of CdO cauliflower-like nanostructure on the removal of Congo red from aqueous solution. *J. Nanostruct. Chem.* **3** (1), 1–8.
- Tan, G. & Xiao, D. 2009 Adsorption of cadmium ion from aqueous solution by ground wheat stems. *J. Hazard. Mater.* **164** (2–3), 1359–1363.
- Tehrani, M. S., Azar, P. A., Namin, P. E. & Dehaghi, S. M. 2013 Removal of lead ions from wastewater using functionalized multiwalled carbon nanotubes with tris(2-aminoethyl)amine. *J. Environ. Protec.* **4** (6), 529–536.
- Tian, X., Li, T., Yang, K., Xu, Y., Lu, H. & Lin, D. 2012 Effect of humic acids on physicochemical property and Cd<sup>2+</sup> sorption of multi-walled carbon nanotubes. *Chemosphere* **89** (11), 1316–1322.
- Tofighy, M. A. & Mohammadi, T. 2011 Adsorption of divalent heavy metal ions from water using carbon nanotube sheets. *J. Hazard. Mater.* **185** (15), 140–147.
- Velickovic, Z. S., Bajic, Z. J., Ristic, M. D., Djokic, V. R., Marinkovic, A. D., Uskokovic, P. S. & Vurna, M. M. 2013 Modification of multi-wall carbon nanotubes for the removal of cadmium, lead and arsenic from wastewater. *Digest J. Nanomat. Biostr.* **8** (2), 501–511.
- Vukovic, G. D., Marinkovic, A. D., Colic, M., Ristic, M. Đ., Aleksic, R., Peric-Grujic, A. A. & Uskokovic, P. S. 2010 Removal of cadmium from aqueous solutions by oxidized and ethylenediamine-functionalized multi-walled carbon nanotubes. *Chem. Eng. J.* **157** (1), 238–248.
- Vukovic, G. D., Marinkovic, A. D., Skapin, S. D., Ristic, M. Đ., Aleksic, R., Peric-Grujic, A. A. & Uskokovic, P. S. 2011 Removal of lead from water by amino modified multi-walled carbon nanotubes. *Chem. Eng. J.* **173** (3), 855–865.
- Waalkes, M. 2003 Cadmium carcinogenesis. *Mutat. Res.* **533**, 107–120.
- Waalkes, M. P. 2000 Cadmium carcinogenesis in review. *J. Inorg. Biochem.* **79** (1–4), 241–244.
- Wang, H. J., Zhou, A. L., Peng, F., Yu, H. & Chen, L. F. 2007 Adsorption characteristic of acidified carbon nanotubes for heavy metal Pb(II) in aqueous solution. *Mat. Sci. Eng. A.* **466** (1–2), 201–206.
- Wang, M., Qu, R., Sun, C., Yin, P. & Chen, H. 2013 Dynamic adsorption behavior and mechanism of transition metal ions on silica gels functionalized with hydroxyl- or amino-terminated polyamines. *Chem. Eng. J.* **221**, 264–274.
- Wang, X., Jia, G. & Wang, H. 2009 Diameter effects on cytotoxicity of multi-walled carbon nanotubes. *J. Nanosci. Nanotechnol.* **9** (5), 3025–3033.
- Wang, X. B., Cai, W. P., Lin, Y. X., Wang, G. Z. & Liang, C. H. 2010 Mass production of micro/nanostructured porous ZnO plates and their strong structurally enhanced and selective adsorption performance for environmental remediation. *J. Mat. Chem.* **20** (39), 8582–8590.
- Weber, W. J. & Morris, J. C. 1963 Intraparticle diffusion during the sorption of surfactants onto activated carbon. *J. Sanit. Eng. Div. Am. Soc. Civ. Eng.* **89** (1), 53–61.
- WHO 2008 *Guidelines for Drinking Water Quality: Recommendations*, vol. 1, 3rd edn, World Health Organization, Geneva, Switzerland.
- Wildgoose, G., Banks, C., Leventis, H. & Compton, R. 2006 Chemically modified carbon nanotubes for use in electroanalysis. *Microchim. Acta* **152** (3–4), 187–214.
- Wu, X., Liang, Y., Jin, T., Ye, T., Kong, Q., Wang, Z., Lei, L., Bergdahl, I. A. & Nordberg, G. F. 2008 Renal effects evolution in a Chinese population after reduction of cadmium exposure in rice. *Environ. Res.* **108** (2), 233–238.
- Xiao, Z. H., Zhang, R., Chen, X. Y., Li, X. L. & Zhou, T. F. 2012 Magnetically recoverable Ni@carbon nanocomposites: Solid-state synthesis and the application as excellent adsorbents for heavy metal ions. *Appl. Surf. Sci.* **263**, 795–803.
- Yang, B., Gong, Q., Zhao, L., Sun, H., Ren, N., Qin, J., Xu, J. & Yang, H. 2011 Preconcentration and determination of lead and cadmium in water samples with a MnO<sub>2</sub> coated carbon nanotubes by using ETAAS. *Desalination* **278** (1–3), 65–69.
- Yang, K. & Xing, B. S. 2007 Desorption of polycyclic aromatic hydro-carbons from carbon nanomaterials in water. *Environ. Pollut.* **145** (2), 529–537.
- Yang, S., Guo, Z., Sheng, G. & Wang, X. 2012 Investigation of the sequestration mechanisms of Cd(II) and 1-naphthol on discharged multi-walled carbon nanotubes in aqueous environment. *Sci. Total Environ.* **420** (1), 214–221.
- Yin, Y. F., Mays, T. & McEnaney, B. 1999 Adsorption of nitrogen in carbon nanotube arrays. *Langmuir* **15** (25), 8714–8718.
- Zhao, G., Li, J., Ren, X., Chen, C. & Wang, X. 2011a Few-layered graphene oxide nanosheets as superior sorbents for heavy metal ion pollution management. *Environ. Sci. Technol.* **45** (24), 10454–10462.
- Zhao, X., Lv, L., Pan, B., Zhang, W., Zhang, S. & Zhang, Q. 2011b Polymer-supported nanocomposites for environmental application: A review. *Chem. Eng. J.* **170** (2–3), 381–394.

First received 29 January 2014; accepted in revised form 22 June 2014. Available online 21 July 2014